

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau

(43) International Publication Date
25 June 2020 (25.06.2020)



(10) International Publication Number
WO 2020/127039 A1

(51) International Patent Classification:

C21C 1/02 (2006.01) C21C 7/064 (2006.01)
C21C 5/06 (2006.01) C21C 5/00 (2006.01)
C21C 5/36 (2006.01) C21C 5/54 (2006.01)

(21) International Application Number:

PCT/EP2019/085338

(22) International Filing Date:

16 December 2019 (16.12.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

18213132.6 17 December 2018 (17.12.2018) EP

(71) Applicant: **S.A. LHOIST RECHERCHE ET DEVELOPPEMENT** [BE/BE]; Rue Charles Dubois 28, 1342 Ottignies-Louvain-la-Neuve (BE).

(72) Inventors: **PERRIN, Éric**; Square Jean Thebaud 17, 75015 Paris (FR). **CHUNLAMANI, Souliyann**; Place des Martyrs 18, 1000 Bruxelles (BE).

(74) Agent: **CALYSTA NV**; Lambroekstraat 5A, 1831 Diegem (BE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: PROCESS FOR MANUFACTURING A SLAG CONDITIONING AGENT FOR STEEL DESULFURIZATION

(57) Abstract: Process for manufacturing a slag conditioning agent for steel desulfurization wherein a dried slag material obtained from secondary steelmaking process is mixed with quicklime particles to produce a slag conditioning agent.



WO 2020/127039 A1

**« PROCESS FOR MANUFACTURING A SLAG CONDITIONING AGENT FOR STEEL
DESULFURIZATION »**

Technical field

The present invention is related to a process for manufacturing a slag conditioning agent for steel desulfurization and to said slag conditioning agent, more particularly to be used in a steel desulfurization process. The process
5 further includes steps of valorizing by-products for agriculture applications, sintering applications or slag stabilization in steelmaking.

Technological background of the invention

Steelmaking is divided in two sequential metallurgies, the primary steelmaking and the secondary steelmaking.

10 Primary steelmaking comprises two major industrial processes.

A first major industrial process for producing steel is the basic oxygen steelmaking process. This process comprises a first step of pelletizing iron ore to provide pellets having a certain porosity, a certain mechanical resistance and a shape allowing flowing of hot air in a blast furnace during the following step
15 of smelting. Alternatively, the first step can be the sintering of iron ore oxides including agglomeration of carbon and minerals in order to have a targeted permeability allowing flowing of hot air in a blast furnace during the step of smelting.

In the step of smelting, coke, pelletized and/or sintered iron ore and a
20 fluxing agent are charged into a blast furnace. Combustion of coke with hot air in the blast furnace provides carbon monoxide which reduces the iron oxide into elemental iron with emissions of carbon dioxide.

The reduced iron obtained during the smelting process has high carbon content and is also known as "pig iron". A slag containing the gangue is formed
25 and floats over the pig iron.

This slag of blast furnace is removed from the pig iron and is generally valorized for cement products.

The molten pig iron is then transferred to a converter comprising a bed of scrap and a flow of pure oxygen is introduced through a water-cooled lance
5 in the converter to oxidize the remaining carbon and other residues present in the scrap and pig iron.

The second major industrial process in the primary metallurgy for producing steel is the electric arc furnace steelmaking. In an electric arc furnace, scrap is loaded, or direct reduced iron is charged into the furnace to
10 produce a batch of steel by electric arc. Fluxes are also added to remove impurities.

Both first and second major industrial processes produced steel which can be used as such or can be further processed through secondary metallurgy, such as for example ladle metallurgy in order to be further purified and
15 improved in terms of properties.

During the ladle metallurgy, there is also two main routes that are typically present, the first route is a route during which sulfur-based compounds are removed and the second route is a route where sulfur-based compound are not removed, the choice between the first and second route
20 depending on the final properties expected in the final steel.

Calcium aluminate is commonly used in combination with quicklime and elemental aluminum for the desulphurization of steel in the secondary metallurgy, i.e. in ladle metallurgy mainly. Calcium aluminate is a metallurgical flux which achieves rapid formation of the slag.

25 **Prior art**

Document WO2017/009581 discloses the state of the art of manufacturing calcium aluminate and a process for manufacturing calcium aluminate. All of these processes involve the step of mixing a source of calcium

and a source of aluminum followed by a step of heating the mixture at elevated temperatures comprised between 1300 and 1700°C.

CN106148633 discloses calcium aluminate based coating agent for controlling the aluminum content in steel.

5 US7811379 discloses a process for manufacturing calcium aluminate product from a composition of liquid ladle slag using the latent heat released by the slag.

10 KR20170106597 discloses a process for the desulfurization for molten iron using a ladle slag with quicklime mixed together to replace the use of fluorite being environmental pollution material. The composition disclosed comprises 80-85 wt% of quicklime and 5-17% of aluminum-by-products and 3-15 wt% of ladle slag.

15 Document EP2835018 discloses a process for obtaining calcium aluminate from dry waste from the treatment of saline dross produced in the metallurgy of secondary aluminum. The dry waste has a composition comprising between 50 and 80 wt% of Al_2O_3 , 3 to 15wt% of SiO_2 , 2 to 10 wt% of MgO , 0.5 to 5 wt% of CaO and below 0.4wt% of TiO_2 and MnO . It is well understood by the man skilled in the art that the amounts of this list of compounds corresponds to the amounts obtained by elemental analysis and
20 each element is expressed under his form of oxide. The dry waste is mixed with CaO and/or a CaO precursor and then heated in a furnace at temperatures above 1100°C to obtain the calcium aluminate.

25 Document US4490173 discloses a steelmaking additive composition comprising from 25 to 50 wt% of lime and 75 to 50 wt% of a compound selected from the group consisting of bauxite and mixture of calcium aluminate and bauxite. The process for manufacturing this composition and the provenance of the raw materials are not mentioned. Despite it is suggested to use such a composition in a process of steelmaking, no explicit results showing substantial improvements relative to other compositions are disclosed.

US5397379 discloses a process wherein a ladle metallurgy furnace (LMF) slag is prepared for reuse in ladle addition by removing magnetically metallics in desulfurization. However, according to this document, the use of the LMF in further desulfurization seems to not be efficient enough in term of
5 ration cost/operation

There is a need for providing a metallurgical flux for a process of steel desulfurization, preferably in ladle furnace, obtainable by a cost-effective process without requiring high energy consumption nor expensive raw materials.

10 **Brief summary of the invention**

The present invention is related to a process for manufacturing a slag conditioning agent for steel desulfurization. The process according to the invention comprises the steps of:

- 15 - providing a slag material obtained from secondary steelmaking process, in particular a slag material obtained after Al-killing steel process, said slag material comprising at least calcium, aluminum, iron, moisture and a phase of calcium aluminate;
- 20 - mixing said slag material with quicklime particles having a predetermined maximum particle size, and drying said slag material by having at least a part of the quicklime particles reacting at least partially with a moisture contained in the slag material with obtaining a first blend comprising slag material, hydrated lime and optionally unreacted quicklime,
- 25 - sieving said first blend at a cut-size superior or equal to said predetermined maximum particle size of said quicklime to remove a passing fraction of said first blend from a retained dried fraction of said first blend, said passing fraction having a maximum particle size lower than said cut-size and comprising a majority of said hydrated lime; and

- 5 - mixing said retained dried fraction with a composition having an Al_2O_3 mass fraction of at least 80 wt% relative to the weight of the composition, and collecting a slag conditioning agent having an equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ comprised between 0.55 and 1.5, preferably between 0.55 and 1, more preferably between 0.55 and 0.7.

The term “slag material” refers to a slag obtained from secondary steelmaking process, in particular the slag obtained after Al-killing steel process.

10 Indeed, whether molten steel comes from a basic oxygen furnace (BOF) or an electric arc furnace (EAF), it must be deoxidized. Deoxidation is generally performed for the purpose of reducing the dissolved oxygen content of the molten steel to the amount required by the ultimate quality of the steel product. To achieve deoxidation, specified amounts of deoxidizing agents are
15 added to the molten steel, generally, carbon, manganese, silicon or aluminum. The deoxidizing agents can be used alone or in combination.

The slag material used in the present invention refers to a slag obtained in the secondary steelmaking where at least aluminum has been added for deoxidizing the steel, alone or in combination with other deoxidizing agents (Al-
20 killing steel process).

The term “slag conditioning agent” refers to an agent obtained by the process according to the present invention for use in a steel desulfurization process wherein a slag is formed by addition of such slag conditioning agent, preferably in combination with quicklime and elemental aluminum for allowing
25 the reduction of iron, with oxidation of aluminum into Al_2O_3 and production of calcium sulfur in the slag.

The term “a majority of said hydrated lime”, within the meaning of the present invention describe the main part of hydrated lime not sticking to or not embedded within the retained dried fraction, i.e. typically as from 90 wt%,

preferably as from 95 wt% or even above 98 wt%, even more than 99 wt% of said hydrated lime being produced.

The term "CaO, Al₂O₃, Fe₂O₃,... or more generally any metal oxide (MeO) equivalent", within the meaning of the present invention means that the semi-quantitative chemical analysis giving the relative mass fraction of calcium, aluminum and iron, ...or even the metal Me, determined by XRF (as described in EN 15309) are reported in equivalent weight of CaO, Al₂O₃, Fe₂O₃, ... or MeO equivalent by weight.

The terms "equivalent mass ratio CaO/Al₂O₃" means accordingly within the meaning of the present invention, the ratio of the equivalent in weight of CaO divided by the equivalent in weight of Al₂O₃.

The present invention allows to produce a slag conditioning agent based on recycled slag material from secondary steelmaking process, in particular the slag obtained after Al-killing steel process, with reduced operation costs with respect to the prior art calcium aluminate slag conditioning agent. Indeed, prior art calcium aluminate required as mentioned before a thermal treatment for having the reaction occurring between bauxite and limestone.

The present invention can be carried out on site or off site. If made on site, it is contemplated according to the present invention to have a movable plant, where series of sieves and mixers as well as the crusher are disposed and connected together and fed by specific slag material from secondary steelmaking process, in particular the slag obtained after Al-killing steel process, even more preferably from ladle furnace without specific desulfurization step. The slag conditioning agent which is produced by the movable plant is then collected and conditioned in bags or in silos for further use in a desulfurization process. The movable plant can be provided on one or more movable platform such as truck platform. In a variant, the slag material is collected on the steelmaking plant, where it has potentially already been partially processed (such as sieved and/or crushed) and transported to a treatment plant to be processed according to the present invention. Further,

the collected slag conditioning agent is conditioned in bags or in silo to be further delivered back on the same steelmaking plant or to another one.

Typical slag material from secondary steelmaking process, in particular the slag obtained after Al-killing steel process comprises a ratio $\text{CaO}/\text{Al}_2\text{O}_3$ above 1.5 while commercial calcium aluminate, such as from thermal treatment of bauxite and limestone have a mean ratio $\text{CaO}/\text{Al}_2\text{O}_3$ around 1.

Slag materials obtained from secondary steelmaking process, in particular the slag comprising at least calcium, aluminum, iron, moisture and a phase of calcium aluminate obtained from Al-killing steel process generally comprises:

- an amount of calcium measured by XRF (X-ray fluorescence) expressed in equivalent CaO comprised between 20 and 45 wt% relative to the weight of the slag material;
- an amount of aluminum measured by XRF expressed in equivalent Al_2O_3 comprised between 10 and 45 wt% relative to the weight of the slag material; and
- an amount of iron measured by XRF expressed in equivalent Fe_2O_3 of at least 2 wt% relative to the weight of the slag material
- and wherein at least a part of said amount of calcium and at least a part of said amount of aluminum is present in said calcium aluminate phase.

Such slag materials are low cost materials. A more detailed analysis of those slag materials by XRD (X-ray diffraction) shows that they comprise various phases of compounds including calcium aluminates and calcium ferrites.

It has been surprisingly identified according to the present invention that mixing a dried recycled slag material with a composition having an Al_2O_3 mass fraction of at least 80 wt% relative to the weight of the composition, produces a slag conditioning agent very efficiently, without requiring thermal treatment.

The composition having an Al_2O_3 mass fraction of at least 80 wt%, measured by XRF, can be obtained from bauxite or preferably from recycling wastes of alumina concrete or a mix thereof. The XRF analysis (X-ray fluorescence spectrometry) is described in EN 15309.

5 Despite the equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ in the recycled slag material is high relative to the desired equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ in the slag conditioning agent, it was made possible according to the present invention to produce in a method wherein quicklime is added, a slag conditioning agent with similar efficiency in term of desulfurization than the
10 commercially available calcium aluminate such as those obtained from bauxite and limestone, but less expensive and involving recycled material (also reducing costs of the operations). Indeed, according to the present invention, the step of drying the slag material with quicklime, followed by the sieving of said first blend to remove a passing fraction of said first blend from a retained dried
15 fraction of said first blend, said passing fraction having a maximum particle size superior or equal to said predetermined maximum particle size of the quicklime and comprising a major portion of said hydrated lime, allow sufficient drying rate and dispense the use of a furnace for drying the slag material and thereby reduces the operation costs and the size of the production plant. The major
20 amount of quicklime added for drying the slag material is removed during the said step of sieving said first blend, mainly under the form of hydrated lime.

Additional benefits of the process for manufacturing the slag conditioning agent according to the present invention is that the slag conditioning agent has advantageously a relative low melting point to provide
25 a liquid medium in the slag wherein reactions of desulphurization are facilitated.

It has been found that the use of the slag conditioning agent obtained by the process according to the invention in combination with quicklime and reducing agents in a steel desulphurization process is as effective in term of

desulfurization of steel that the use of substantially pure compounds of calcium aluminate combined with quicklime and reducing agents such as in prior art.

It is of common practice in the art of steel desulphurization to avoid flux comprising iron oxide because the presence of iron oxide requires increasing
5 the consumption of expensive reducing agent in the process. According to the invention, the amount of iron in the slag material, measured by XRF and expressed in equivalent Fe_2O_3 is allowed to be up to 20 wt%.

Above this value of 20 wt%, the slag conditioning agent thereby obtained would have to be utilized in the steel desulphurization process with
10 too much reducing agent and it wouldn't be economically worth. In the slag material, some of the iron is present under the form of calcium ferrites which are beneficial for the fluidizing the slag in the steel desulfurization process.

Preferably, the XRD analysis of the slag material shows significant presence of calcium aluminate, preferably at least 5 wt% in weight of the slag
15 material. The slag material comprises an amount of calcium "Ca" expressed in CaO equivalent comprised between 20 and 45 wt% measured by XRF analysis and an amount of Al expressed in Al_2O_3 equivalent comprised between 10 and 45 wt% measured by XRF analysis and wherein the equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ is superior or equal to 1 (typical of the slags obtained by the process
20 Al killing process). The weight % are mentioned relative to the weight of the slag material.

It is important that the slag material does not contain or contain the less possible amount of sulfur, titanium oxide or boron, preferably under 1 wt%, more preferably under 0.5 wt% more preferably under 0.2 wt% in weight of the
25 slag material, for the avoiding any detrimental effect on the mechanical or rheological properties of steel.

In an embodiment of the process for manufacturing the slag conditioning agent according to the invention, when the slag material comprises an amount of iron below 5 wt% relative to the weight of the slag

material, measured by XRF analysis, the targeted equivalent mass ratio of $\text{CaO}/\text{Al}_2\text{O}_3$ is preferably comprised between 0.55 and 0.9, preferably between 0.55 and 0.7, more preferably between 0.57 and 0.63.

As it is known by the phase diagram of calcium aluminate, the lowest
5 melting point of in this phase diagram is reached when the equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ is comprised between 0.9 and 1.1.

During the desulfurization process, quicklime, elemental aluminum and the slag conditioning agent are introduced in the hot metal, resulting in reduction of iron with production of Al_2O_3 and CaS . Because of the production
10 of Al_2O_3 during the desulfurization process, there is an advantage to provide a slag conditioning agent having an equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ which is slightly higher than 0.5, preferably comprised between 0.55 and 0.9, preferably between 0.55 and 0.7, more preferably between 0.57 and 0.63 so that the production of Al_2O_3 in combination with the use of quicklime during the
15 desulphurization process decreases the equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ in the slag to 0.9 to 1.1 corresponding to the lowest melting point of the phase diagram of calcium aluminates and such that the slag in the process of desulfurization presents a low viscosity facilitating the contact between the different components for the reactions of desulfurization.

20 In another embodiment of the process for manufacturing the slag conditioning agent according to the invention, when the slag material comprises an amount of iron comprised between 5 to 20 wt% relative to the weight of the slag material, in which a substantial amount of iron is present under the form of calcium ferrites, the targeted equivalent mass ratio of
25 $\text{CaO}/\text{Al}_2\text{O}_3$ can be higher than 0.7, preferably lower than 1.5, more preferably lower than 1.4, more preferably lower than 1.

The amount of calcium ferrite measured by XRD analysis is preferably of at least 1 wt%, preferably at least 2 wt%, more preferably at least 3 wt%, in particular more than 4 wt%, and more particularly more than 5 wt%, relative to
30 the weight of the slag material.

The calcium ferrites present in the slag material and therefore in the slag conditioning agent obtained by the process according to the invention, have a relatively low melting point, about 1350°C. Therefore, the calcium ferrites present in the slag conditioning agent participate to the fluidization of the slag during the desulphurization process.

The targeted equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ in the slag conditioning agent can be increased in function of the amount of calcium ferrites, and therefore the amount of composition having an Al_2O_3 mass ratio measured by XRF and relative to the weight of the composition, to be mixed with said dried slag material, can be reduced.

Preferably, the moisture content of the slag material is inferior to 10 wt%, preferably less than 5wt%, more preferably less than 3wt% relative to the weight of the slag material. The less moisture in the slag material, the less quicklime has to be used to dry the slag material.

According to the present invention, the moisture content is measured by loss on drying (LOD) at 105°C.

In a preferred embodiment of the invention, the process according to the invention aims to provide a slag conditioning agent with a predetermined granulometry having :

- a predetermined minimum particle size (a) such as to avoid dispersion of fines during manipulation of the product and/or;
- a predetermined maximum particle size (b) optimized for the pneumatic transport conditions or for the mechanical transport conditions at the steel plant.

The particle size distribution of the slag conditioning agent or any other of particles involved in the process according to the present invention is easily determined by sieving particles on a sieve having a certain mesh allowing or not the passage of at least 90%, preferably at least 95%, even 98 or 99 wt% of the said particles.

The slag material has generally a broad particle size distribution and has to be crushed to obtain particles of slag material having a maximum particle size (b) corresponding to the maximum predetermined maximum particle size (b) wished for the slag conditioning agent.

5 Preferably, a first sieving step is performed to remove a first fraction of particles that couldn't be crushed under the predetermined maximum particle size (b). Then a second sieving step is performed to remove the fraction under the predetermined minimum size (a) wished for the slag conditioning agent. The passing fraction is valorized for agriculture applications or sintering
10 applications (steel industry).

The fraction of the crushed slag material having a particle size distribution (a-b) in the range comprised between the minimum (a) and maximum (b) particle size is retained and dried by mixing with quicklime having a particle size distribution inferior to the minimum particle size (a). Preferably,
15 the quicklime used for drying said fraction of crushed slag material (a-b) is a high reactive quicklime having a time of reactivity t_{60} with water inferior to 2min, as measured according to the water reactivity test of European standard EN459-2:2010E.

More preferably, the said quicklime has a BET specific surface area
20 superior to $0.8 \text{ m}^2/\text{g}$, measured by nitrogen adsorption manometry after vacuum degassing at 190°C for at least 2 hours, calculated by the multiple-point BET method as described in standard ISO 9277:2010 E.

In any case, the particle size distribution of the quicklime must be lower than the predetermined minimum size (a) wished for the slag conditioning
25 agent. Preferably, the particle size distribution of said quicklime is inferior to 1 mm, more preferably inferior to $500 \mu\text{m}$, more preferably inferior to $200 \mu\text{m}$ and even more particularly inferior to $90 \mu\text{m}$.

The particle size distribution of said quicklime means that more than 90 wt% of the particles have a particle size inferior to 1 mm, more preferably

inferior to 500 μm , more preferably inferior to 200 μm and even more particularly inferior to 90 μm , measured by sieving analysis.

It is advantageous to provide a quicklime having particles with a high reactivity characterized by the said t_{60} , a small particle size distribution and
5 optionally also a high specific surface area such as to remove efficiently the moisture from the crushed slag material with the less amount as possible of quicklime and such that the so-formed hydrated lime from quicklime can be easily removed in the subsequent step of sieving. In that subsequent step of
10 sieving, the blend comprising crushed slag material and hydrated lime is sieved to discard a passing fraction of particles having a particle size inferior to the minimum particle size (a) wished for the slag conditioning agent.

In a variant, quicklime has particles of lime kiln dust, showing also efficiency for removing the moisture of the crushed slag material with an amount such that so formed hydrated lime can be easily removed in the
15 subsequent step of sieving. In that subsequent step of sieving, the blend comprising crushed slag material and hydrated lime kiln dust is sieved to discard a passing fraction of particles having a particle size inferior to the minimum particle size (a) wished for the slag conditioning agent.

By the terms "lime kiln dust", it is meant according to the present
20 invention a lime co-byproduct from quicklime manufacturing which contain typically at least 50 wt% of quicklime particles, preferably 60 wt% of quicklime particles, more preferably at least 70 wt% relative to the weight of the lime kiln dust. The lime kiln dust can contain calcium carbonate residues from unburned limestone and/or partial re-carbonation of lime and other impurities from the
25 limestone, notably silica. Typically, a small amount of hydrated lime can be found in the lime kiln dust, such as less than 8 wt%, relative to the weight of the lime kiln dust. Typically, lime kiln dust has an average medium particle size d_{50} lower than 60 μm , preferably lower than 50 μm , more preferably lower than 40 μm .

The discarded fraction comprises high amounts of hydrated lime and some further elements coming from the slag material. That discarded fraction is valorized for applications in sintering. The retained dried (coarse) fraction comprises mainly particles of slag material having a desired range of particle size (a-b) and a minor amount of hydrated lime, preferably inferior to 1%. The retained fraction is mixed with a composition having an Al_2O_3 mass fraction of at least 80 wt% and having the same desired range of particle size (a-b), to obtain as a final product, a slag conditioning agent having a desired range of particle size (a-b) and a targeted equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$.

Exemplary values of particles size (a) are comprised between 0,5 mm and 5 mm, preferably between 1 mm and 4 mm and can be for example 1 mm, 2 mm or even 3 mm.

The maximum particle size of quicklime shall be chosen independently of the cut-size of the sieving but should respect the condition that maximum particle size of quicklime is lower than or equal to the cut-size of the sieving.

Exemplary values of particles size (b) are comprised between 10 mm and 25 mm, preferably between 12 mm and 20 mm and can be for example 12 mm, 14 mm or even 15 mm.

In an embodiment of the invention, the first step of sieving before addition of quicklime can be suppressed, but in this case, more quicklime must be used for drying the slag material which represents an additional cost for drying slag particles that have to be discarded thereafter.

Other embodiments of the process according to the present invention are mentioned in the appended claims.

The present invention also relates to a slag conditioning agent, in particular for a process of steel desulfurization, such as in ladle steelmaking, comprising phases of calcium aluminate and having an equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ comprised between 0.55 and 1.5, preferably between 0.55 and 1, more preferably between 0.55 and 0.7, said slag conditioning agent having an

iron content measured by XRF and expressed in equivalent Fe_2O_3 of at least 2 wt%, preferably at least 3 wt%, and at most 20 wt%, relative to the weight of the slag conditioning agent and an aluminum content expressed in equivalent Al_2O_3 of at least 30 wt%, more preferably of at least 40 wt%.

5 In an advantageous embodiment, the slag conditioning agent comprise an amount of calcium ferrites measured by XRD of at least 1 wt%, more preferably at least 2 wt%, more preferably at least 5 wt% relative to the weight of the slag conditioning agent.

According to the present invention, said slag conditioning agent has a
10 particle size distribution comprised between a minimum value and a maximum value, said minimum value being of at least 1 mm.

According to a variant of the present invention, said slag conditioning agent has a particle size distribution comprised between a minimum value and a maximum value, said maximum value being of maximum 20mm.

15 Other embodiment of the slag conditioning agent according to the present invention are mentioned in the appended claims.

The present invention also relates to a use of a slag conditioning agent according to the present invention, for example obtained by the process according to the present invention in a process of steel desulfurization.

20 Preferably, the slag conditioning agent according to the present invention is used at an amount of 2 to 16 kg, preferably from 2,5 to 12 kg, more preferably from 3 to 10 kg, even more preferably below 8 kg and more particularly less than 6 kg of slag conditioning agent/ton of steel preferably in combination with elemental aluminum in amounts less than 100 g/t of steel,
25 preferably less than 80 g/t, more preferably less than 70 g/t, more preferably less than 60 g/t of steel, more particularly less than 50 g/t and even more preferably less than 40 g/t steel and an amount of quicklime of less than 12 kg/t steel, preferably less than 10 kg/t steel and even more preferably less than 8 kg/t steel.

Other use of the slag conditioning agent is mentioned in the appended claims.

Other characteristics and advantages of the present invention will be derived from the non-limitative following description, and by making reference
5 to the drawings and the examples.

Detailed description of the invention

Examples.-

An example of a process for manufacturing a slag conditioning agent according to the present invention is described herein.

10 25,2 ton of a slag obtained from secondary steelmaking process, in particular the slag obtained after Al-killing steel process, is crushed to obtain slag particles under 14 mm. After the step of crushing, a first sieving can be performed for removing the coarse particles that couldn't be crushed under 14 mm and those coarse particles can be re-injected in the crusher used for a
15 further crushing in another production batch. 4 t of crushed slag particles are discarded. Then a second step of sieving is performed on the 21,2 t of crushed slag material particles to remove the fraction of crushed slag particles below 3 mm. 5,2 t of crushed slag particles under 3 mm are discarded and valorized for slag conditioning in steelmaking applications (passing fraction).

20 The elemental composition of the fraction (retained fraction) of slag material having a particle size in the range comprised between 3 and 14 mm is measured by XRF on samples dried at 105°C. This fraction comprises 24.6 wt% of Aluminum expressed in equivalent Al_2O_3 , 41 wt% of calcium expressed in equivalent CaO, 16 wt% of iron expressed under equivalent Fe_2O_3 , 5.5 wt% of
25 magnesium expressed in equivalent MgO, 3 wt% of manganese expressed in Mn_2O_3 , 7.1 wt % of silicon expressed in equivalent SiO_2 and other impurities.

This fraction has a loss on drying (LOD) at 105°C of 1.84%, corresponding to the moisture of the fraction and a loss on ignition (LOI) at 900°C of 3.3 wt%

which may correspond to the loss of hydroxides and/or carbonates in the phases present in the fraction. XRD analysis shows various phases of compounds including calcium aluminates and calcium ferrites.

16 t of the fraction of slag particles between 3 and 14 mm is then dried
5 by mixing with 1.6 t of high reactive quicklime having a particle size under 1mm, a BET specific surface area superior to 0.8 m²/g and a reactivity t₆₀ with water below 1 minute. The blend of slag particles and hydrated lime thereby obtained is sieved to remove the passing fraction of particles under 3 mm of particle size.

About 1.8 t of particles under 3 mm particle size is discarded. This latter
10 fraction of discarded particles is valorized in applications of agriculture, sintering and slag conditions for steelmaking.

The elemental composition of the retained fraction at 3 mm (15.8 ton) of the blend of slag particles with quicklime having a particle size in the range comprised between 3 and 14 mm is measured by XRF on samples dried at
15 105°C. This fraction comprises 20.7 wt% of Aluminum expressed in equivalent Al₂O₃, 46.1 wt% of calcium expressed in equivalent CaO, 15.6 wt% of iron expressed under equivalent Fe₂O₃, 6.4 wt% of magnesium expressed in equivalent MgO, 2.7 wt% of manganese expressed in Mn₂O₃, 6.4 wt % of silicon expressed in equivalent SiO₂ and other impurities. This fraction has a loss on
20 drying (LOD) at 105°C inferior to the level of detection which means that the fraction is well dried and a loss on ignition (LOI) at 900°C of 4.58 wt% which may correspond to the loss of hydroxides and/or carbonates in the phases present in the fraction or in the added quicklime.

The same analyses are performed on the fraction of the blend of slag
25 particles mixed with quicklime having a particle size below 3mm. A sample of this fraction comprises 7.5 wt% of Aluminum expressed in equivalent Al₂O₃, 70.4 wt% of calcium expressed in equivalent CaO, 6.9 wt% of iron expressed under equivalent Fe₂O₃, 6.2 wt% of magnesium expressed in equivalent MgO, 0.9 wt% of manganese expressed in Mn₂O₃, 6.4 wt % of silicon expressed in
30 equivalent SiO₂ and other impurities. This fraction has a loss on drying (LOD) at

105°C of 0.07% and a loss on ignition (LOI) at 900°C of 24 wt% which to correspond to the loss of water molecules from hydrated lime. These measurements show that the moisture has been well removed.

15 15.8 t of the fraction of the blend of slag particles with quicklime having a particle size in the range comprised between 3 and 14 mm is then mixed with 6.8 t of an alumina composition previously sieved to the same range of particle size between 3 and 14 mm, to obtain the slag conditioning agent according to the invention. The XRF analysis of the alumina composition shows that it
10 comprises 86 wt% of aluminum expressed in equivalent Al_2O_3 , 5.3 wt% of magnesium expressed in equivalent MgO , 5.5 wt% of silicon expressed in SiO_2 equivalent, 2 wt% of zirconium expressed in ZrO_2 equivalent, and other impurities.

The final elemental composition of the slag conditioning agent is measured by XRF analysis and contains 42.9 wt% of aluminum expressed in
15 equivalent Al_2O_3 , 28.9 wt% of calcium expressed in equivalent CaO , 12.8 wt% of iron expressed under equivalent Fe_2O_3 , 4.1 wt% of magnesium expressed in equivalent MgO , 2.2 wt% of manganese expressed in equivalent Mn_2O_3 , 7,2 wt % of silicon expressed in equivalent SiO_2 and other impurities. The equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ is of 0.67. XRD analysis still shows various phases of
20 compounds including calcium aluminates and calcium ferrites in less amounts than in the slag material because of the dilution effect with the alumina composition.

In a steel desulfurization process, the slag conditioning agent obtained according to the process of the present invention is used in an amount of 3 to
25 5kg/t of steel, in combination with elemental aluminum in amounts of 60g/t steel and a determined amount of quicklime such as 10 kg/t steel. This steel desulfurization process is compared with a typical process wherein substantially pure calcium aluminate with an equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ of 0.5 is used in an amount of 5 kg/t of steel in combination with elemental

aluminum in amounts of 40 g/t of steel and a determined amount of quicklime 10 kg/t steel.

Both processes show the same efficiency in term of desulfurization. Despite the steel desulfurization process using the slag conditioning agent
5 obtained according to the invention requires slightly more elemental aluminum for reducing iron, the additional price of elemental aluminum is compensated by the cost-effective price of the slag conditioning agent compared to the price of substantially pure calcium aluminate.

Additional benefits of the process for manufacturing the slag
10 conditioning agent according to the present invention is that slag material from secondary steelmaking process, in particular the slag obtained after Al-killing steel process, can be recycled. Also, some of the by-products obtained during the process can be valorized in other applications. In the process according to the invention, the step of drying the slag material with quicklime followed by
15 the removal of hydrated lime dispense the use of a furnace for drying the slag material and thereby reduces the operation costs and the size of the production plant.

It should be understood that the present invention is not limited
to the described embodiments and that variations can be applied without going
20 outside of the scope of the appended claims.

« CLAIMS »

1. Process for manufacturing a slag conditioning agent for steel desulfurization comprising the steps of:
- providing a slag material obtained from secondary steelmaking process, in particular a slag material obtained after Al-killing steel process, said slag material comprising at least calcium, aluminum iron, moisture and a phase of calcium aluminate;
 - mixing said slag material with quicklime particles having a predetermined maximum particle size, and drying said slag material by having at least a part of the quicklime particles reacting at least partially with a moisture contained in the slag material with obtaining a first blend comprising slag material, hydrated lime and optionally unreacted quicklime,
 - sieving said first blend at a cut-size superior or equal to said predetermined maximum particle size of said quicklime to remove a passing fraction of said first blend from a retained dried fraction of said first blend, said passing fraction having a maximum particle size lower than said cut-size and comprising a majority of said hydrated lime; and
 - mixing said retained dried fraction with a composition having an Al_2O_3 mass fraction of at least 80 wt% relative to the weight of the composition, and collecting a slag conditioning agent having an equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ comprised between 0.55 and 1.5, preferably between 0.55 and 1, more preferably between 0.55 and 0.7.
2. Process according to claim 1 wherein the said slag material comprising at least calcium, aluminum iron, moisture and a phase of calcium aluminate comprises :

- an amount of calcium measured by X-ray fluorescence expressed in equivalent CaO comprised between 20 and 45 wt% relative to the weight of the slag material;
 - an amount of aluminum measured by XRF expressed in equivalent Al_2O_3 comprised between 10 and 45 wt% relative to the weight of the slag material; and
 - an amount of iron measured by XRF expressed in equivalent Fe_2O_3 of at least 2 wt%, preferably at least 3 wt% relative to the weight of the slag material,
- 10 - and wherein at least a part of said amount of calcium and at least a part of said amount of aluminum is present in said calcium aluminate phase
- 15 3. Process according to claim 1 or claim 2 wherein the said slag material comprises up to 20 wt% of iron expressed in equivalent Fe_2O_3 relative to the weight of the slag material.
- 20 4. Process according to any one of the preceding claims wherein the moisture of said slag material is present at a moisture content inferior to 10 wt%, preferably less than 5wt%, more preferably less than 3wt%, relative to the weight of the slag material.
- 25 5. Process according to any one of the preceding claims wherein the said quicklime particles comprises at least particles having a reactivity with water t_{60} according to the EN 459-2:2010E, inferior to 2 min.
- 30 6. Process according to any one of the claims 1 to 5, wherein the said quicklime particles comprises at least lime kiln dust particles.
7. Process according to any one of the preceding claims wherein the said quicklime particles have a BET specific surface area superior to $0.8 \text{ m}^2/\text{g}$ measured by nitrogen adsorption manometry after vacuum degassing

at 190°C for at least 2 hours, calculated by the multiple-point BET method as described in standard ISO 9277:2010 E.

- 5 8. Process according to any one of the preceding claims wherein the said slag material is crushed and optionally sieved to have a maximum particle size inferior to a maximum value (b).
- 10 9. Process according to any one of the preceding claims wherein the said slag material is sieved to have a minimum particle size superior to a minimum value (a).
- 15 10. Slag conditioning agent for a process of steel desulfurization, comprising phases of calcium aluminate and an equivalent mass ratio $\text{CaO}/\text{Al}_2\text{O}_3$ comprised between 0.55 and 1.5, preferably between 0.55 and 1, more preferably between 0.55 and 0.7, said slag conditioning agent having an iron content measured by XRF and expressed in equivalent Fe_2O_3 of at least 2 wt%, preferably at least 3 wt%, and at most 20 wt%, and an aluminum content expressed in equivalent Al_2O_3 of at least 30 wt%, more preferably of at least 40 wt%.
- 20 11. Slag conditioning agent according to claim 10, comprising an amount of calcium ferrites measured by XRD of at least 1 wt%, more preferably at least 2 wt%, more preferably at least 5 wt% relative to the weight of the slag conditioning agent..
- 25 12. Slag conditioning agent according to claim 10 or claim 11, having a particle size distribution comprised between a minimum value and a maximum value, said minimum value being of at least 1 mm.
- 30 13. Slag conditioning agent according to anyone of the claims 10 to 12, having a particle size distribution comprised between a minimum value and a maximum value, said maximum value being of maximum 20mm.

14. Use of a slag conditioning agent according to any one of the claims 10 to 13, obtained by the process according to any one of the claims 1 to 9 in a process of steel desulfurization.
- 5 15. Use of slag conditioning agent according to claim 14, at an amount of 2 to 16 kg, preferably from 2,5 to 12 kg, more preferably from 3 to 10 kg, even more preferably below 8 kg and more particularly less than 6 kg of slag conditioning agent/ton of steel, preferably in combination with elemental aluminum in amounts less than 100 g/t of steel, preferably less than 80 g/t, more preferably less than 70 g/t, more preferably less than 60 g/t of steel, more particularly less than 50 g/t and even more preferably less than 40 g/t steel and an amount of quicklime of less than 12 kg/t steel, preferably less than 10 kg/t steel and even more preferably less than 8 kg/t steel.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2019/085338

A. CLASSIFICATION OF SUBJECT MATTER
 INV. C21C1/02 C21C5/06 C21C5/36 C21C7/064 C21C5/00
 C21C5/54
 ADD.
 According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 C21C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
 EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CN 106 148 633 A (PANZHUIHUA IRON & STEEL RES INST PANGANG GROUP) 23 November 2016 (2016-11-23) abstract paragraph [0019] claim 3 paragraph [0026]	1-4
X	US 7 811 379 B2 (HARSCO CORP [US]) 12 October 2010 (2010-10-12)	1-14
A	abstract claim 1	15
X	US 5 397 379 A (BARKER BRUCE J [US] ET AL) 14 March 1995 (1995-03-14)	1-14
A	abstract claim 2 column 3, line 6 - line 15	15
	----- -/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search 9 January 2020	Date of mailing of the international search report 21/01/2020
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Vermeulen, Yves

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2019/085338

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	KR 2017 0106597 A (POSCO [KR]) 21 September 2017 (2017-09-21)	1-14
A	abstract paragraph [0047]	15
A	----- EP 2 213 753 A1 (AKAD GORNICZO HUTNICZA [PL]) 4 August 2010 (2010-08-04) claim 1	1-15
A	----- US 7 563 303 B2 (LAFARGE SA [FR]) 21 July 2009 (2009-07-21) abstract	1-15
A	----- CN 105 349 734 A (GANGCHENG GROUP LIANGSHAN RUIHAI IND CO LTD) 24 February 2016 (2016-02-24) abstract	1-15
A	----- Kt Jacob ET AL: "Thermodynamic properties of the calcium ferrites CaFe ₂ O ₄ and Ca ₂ Fe ₂ O ₅ ePrints@IISc", 3 August 2011 (2011-08-03), XP055580312, Retrieved from the Internet: URL: http://eprints.iisc.ac.in/38893/ [retrieved on 2019-04-11] the whole document	11
A	----- FR 2 541 310 A1 (LAFARGE FONDU INT [FR]) 24 August 1984 (1984-08-24) the whole document	1-15
A	----- WO 2007/000433 A2 (LHOIST RESERCH ET DEVELOPPEMENT) 4 January 2007 (2007-01-04) the whole document	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2019/085338

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
CN 106148633	A	23-11-2016	NONE
US 7811379	B2	12-10-2010	AU 2007254026 A1 29-11-2007 EP 2018444 A2 28-01-2009 US 2007266902 A1 22-11-2007 US 2010193733 A1 05-08-2010 WO 2007136914 A2 29-11-2007
US 5397379	A	14-03-1995	CA 2118646 A1 23-03-1995 US 5397379 A 14-03-1995
KR 20170106597	A	21-09-2017	NONE
EP 2213753	A1	04-08-2010	EP 2213753 A1 04-08-2010 PL 213251 B1 28-02-2013
US 7563303	B2	21-07-2009	BR PI0418087 A 17-04-2007 CA 2551270 A1 14-07-2005 CN 1906313 A 31-01-2007 EP 1699940 A1 13-09-2006 FR 2864551 A1 01-07-2005 JP 2007517137 A 28-06-2007 KR 20060127038 A 11-12-2006 UA 84723 C2 25-11-2008 US 2007144306 A1 28-06-2007 US 2008302210 A1 11-12-2008 WO 2005064022 A1 14-07-2005 ZA 200605217 B 25-09-2008
CN 105349734	A	24-02-2016	NONE
FR 2541310	A1	24-08-1984	NONE
WO 2007000433	A2	04-01-2007	AR 056662 A1 17-10-2007 AT 492514 T 15-01-2011 BE 1016661 A3 03-04-2007 BR PI0614047 A2 07-06-2011 CA 2613186 A1 04-01-2007 CN 101370735 A 18-02-2009 CN 103626216 A 12-03-2014 CN 106927491 A 07-07-2017 DK 1896364 T3 28-02-2011 EP 1896364 A2 12-03-2008 ES 2356388 T3 07-04-2011 HR P20110057 T1 30-04-2011 JP 5144509 B2 13-02-2013 JP 2008546631 A 25-12-2008 MA 29642 B1 01-07-2008 PL 1896364 T3 31-05-2011 PT 1896364 E 22-02-2011 RS 51632 B 31-08-2011 SI 1896364 T1 29-04-2011 TW I395713 B 11-05-2013 UA 93682 C2 10-03-2011 US 2009229462 A1 17-09-2009 WO 2007000433 A2 04-01-2007 ZA 200800781 B 24-06-2009