

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization

International Bureau

(43) International Publication Date  
07 June 2018 (07.06.2018)



(10) International Publication Number  
**WO 2018/100064 A1**

(51) International Patent Classification:

C22B 1/24 (2006.01) C22B 1/243 (2006.01)

(21) International Application Number:

PCT/EP2017/080986

(22) International Filing Date:

30 November 2017 (30.11.2017)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

PCT/EP2016/079338

30 November 2016 (30.11.2016) EP

(71) Applicant: **S.A. LHOIST RECHERCHE ET DEVELOPPEMENT** [BE/BE]; rue Charles Dubois 28, 1342 Ottignies-Louvain-la-Neuve (BE).

(72) Inventors: **DA COSTA, Eduardo**; Avenue des Cerfs 18, 4031 Angleur (BE). **PELLETIER, Marc**; Rue de l'Alouette 3 bis, 94160 Saint-Mandé (FR).

(74) Agent: **GEVERS PATENTS**; Holidaystraat 5, 1831 Diegem (BE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: METALLIC ORE PELLETS

(57) Abstract: The present invention concerns the use of a magnesium-including compound as binder for producing metallic ore fluxed pellets, in particular iron ore fluxed pellets, said magnesium-including compound comprising semi-hydrated dolime fitting the general formula  $a\text{Ca}(\text{OH})_2.b\text{Mg}(\text{OH})_2.c\text{MgO}$ , a, b, and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime.



WO 2018/100064 A1

“Metallic ore pellets”

The present invention relates to metallic ore fluxed pellets, in particular iron ore fluxed pellets.

According to the present invention, it is meant by the terms  
5 “metallic ore fluxed pellets”, pellets made from metallic ore coming from metal ore mines. The term “metallic” is a general term which includes the ferrous, also called iron, and the non-ferrous metal ore. The non-ferrous metal ore commonly contains metals such as chromium, manganese, nickel, lead, tin, copper, etc.

10 The iron (ferrous) ore mainly contains iron, about 60% by weight or above, but may also contain other metals such as titanium and manganese in combination with iron.

Metallic ore pellets are produced from fine metallic concentrate containing at least 60 % by weight of metals. Metallic ore  
15 concentrate, also simply called concentrate, is the product obtained by finely grinding raw ore in a grinding operation after which the gangue (impurities) is removed. The resulting product is therefore a concentrate of metal component. The remaining impurities which can be present in the concentrate are for example silicates, aluminates, phosphates, sulphates.

20 Iron ore pellets are made from magnetitic, hematitic, limonitic sideritic concentrates containing at least 60% by weight of iron.

The fine metallic concentrate is firstly granulated in a vessel (container) like a drum or a disk (pan) during a balling process, to form the so-called green pellets which are in fact crude pellets. These green pellets  
25 are then hardened by heating in an induration furnace which is typically divided in three zones; the drying zone at about 300°C, the firing zone at about 1300 °C and the cooling zone. After the hardening process, the pellets may be called fired pellets and are suitable for handling in bulk and charging into a metallurgical reactor, for example a blast furnace  
30 (shortened BF) or a direct reduction reactor (shortened DR), the direct reduction reactor being used before an electric arc furnace in a plant.

It is known to use naturally available minerals, such as olivine, dunite, pyroxenite, limestone or dolomite, as fluxes, also called fluxing agents, to improve the metallurgical properties of the fired pellets. It is indeed known that the properties and the chemical composition of the green pellets have an impact on the quality of fired pellets when used in metallurgical reactor. The metallic ore pellets containing fluxes are also called metallic ore fluxed pellets or just fluxed pellets. The properties of the fluxed pellets depend on the nature of the above fluxes which are physically and chemically different and which contain different types and quantities of gangue materials, such as silica and/or alumina, etc. which are considered as impurities in the pellets.

In the production of fluxed pellets, carbonates and/or silicates are commonly used. Carbonates present the disadvantage for the pellet producer of consuming energy for their calcination, as well as the emission of carbon dioxide. In the production of calcitic fluxed pellets, the use of calcium carbonate (limestone) as flux is common. In the production of magnesian fluxed pellets, magnesium silicate, like olivine or pyroxenite has been privileged as the flux.

Binders are used in the production of fluxed pellets in order to allow the formation of the green pellets by balling and then withstand the mechanical and thermal stresses of the handling in their production process in particular in the induration furnace (in the drying, firing and cooling zones).

Bentonite, a type of clay, has been the binder of choice since the inception of the production of metallic ore fluxed pellets. An existing alternative to the bentonite is the use of organic binders like those based on carboxymethylcellulose or polyacrylamide, which are however more expensive and hinder the achievement of good mechanical properties in the final pellets.

The present invention aims at focusing on the use of alternative binders for the manufacturing of metallic ore fluxed pellets, in particular iron ore fluxed pellets.

The document of J. Pan et al. relates to the production in  
5 laboratory of calcitic fluxed pellets made from the mix of pre-treated iron fine ore, binder and limestone as fluxes (see Iron Ore conference / Perth, WA, 11-13 July 2011, J Pan, D Q Zhu, M Emrich, T J Chun and H Chen, "Improving the fluxed pellets performance by hydrated lime instead of bentonite as binder"). The binders which are compared in this document  
10 are bentonite and hydrated lime and the mechanical properties of the resulting fluxed pellets are analysed. This document concludes that the replacement of bentonite by hydrated lime as binder improves the physical properties and the compressive strength of fired pellets and also plays a role in improving the metallurgical performance of fired pellets.

15 However, this document also discloses that in order to observe this improvement in the compressive strength of the fired pellets in the presence of hydrated lime, the preheating temperature during the induration process of the green pellets has to be controlled and brought up to 1100 °C. Indeed, the compressive strength of the fired pellets made  
20 from preheated pellets with bentonite is higher than the one of those made from preheated pellets containing hydrated lime when the preheating temperature was less than 1050 °C.

The document of Cribbes and Kestner (see Research Engineer, Dravo Corportion, Pittsburgh, Pennsylvania, Chapter 16, pages  
25 272-285, 1977 "Some factors influencing iron ore fired pellet quality" by James D. Cribbes and Daniel W. Kestner) shows that it is possible to use hydrated lime as a substitute for limestone as flux and for bentonite as binder and still obtain pellets presenting reasonable physical properties. In this document, fluxed pellets containing bentonite and hydrated lime are  
30 compared to fluxed pellets containing only hydrated lime. They noticed that, at the optimum balling moisture for pellets containing bentonite plus

limestone, the pellets made only with hydrated lime produce, after the hardening process, fired pellets having a fuzzy, uneven surface. They also found out that it is necessary to reduce the green pellet moisture for pellets containing only hydrated lime in comparison with the pellets containing  
5 bentonite, to obtain fired pellets presenting a good fired strength after the hardening process. These results showed that the control of the balling parameters such as moisture of the green pellets is more difficult with the use of hydrated lime as flux and binder and that properties of the green pellets when not well controlled can have an impact on the quality of fired  
10 pellets.

The document of Gielen relates to the industrial production of pellets made from hematitic concentrate (see Society of mining engineers of aime, Colorado, 1983, "Quality improvements and energy savings in iron ore pelletizing" by H.H. Gielen, H.S. Heep, M. R. Hohensee, H. G.  
15 Papacek, V. V. Arnim). In this document, they stated that hydrated lime is by no means a good substitute for bentonite as a binder in fluxed pellets. Green pellets containing hydrated lime as a binder had a strong tendency to stick, causing a lot of difficulties with clogged screen decks. They highlighted that, with improvements achieved in the filter section (filter  
20 cake) during a filtration step of the fine concentrates and at the same time a partial substitution of hydrated lime by limestone in the composition of the green pellets, the difficulties during the balling step were reduced.

Because of the difficulties above mentioned encountered when other binders than bentonite have been tested, over time, bentonite  
25 turned out to be the binder of choice in the production of fluxed pellets notably because it enhances the balling process by controlling the moisture content of the green pellets. Indeed, the balling process and more precisely the balling rate is, amongst others, controlled by the moisture content of the raw mixture used to produce green pellets. Bentonite has  
30 been found to more easily regulate the moisture content during the balling process.

However, although bentonite seems to be inescapable for producing metallic fluxed pellets with good physical properties, it presents the drawback of bringing more impurities, mainly silica and alumina, to the green pellets. These impurities withstand the induration process and can  
5 be found in the fired pellets. The addition of impurities such as silica or alumina to the fired pellets causes thereafter the increase of the amount of slag in the metallurgical furnace (notably the blast furnace or the electric arc furnace) which is not desirable.

The present invention further relates to metallic ore fluxed  
10 pellets, in particular iron ore fluxed pellets containing magnesium-including compound as binder.

By the terms "magnesium-including compound", it is meant in the present invention, a compound based on magnesium such as magnesium hydroxide, calcium magnesium tetra hydroxide, calcium  
15 magnesium (di)hydroxide oxide and mixtures thereof.

Further, the basicity of the fired pellets has to be controlled by controlling the fraction between Ca and/or Mg compounds (expressed as oxides CaO and/or MgO) on the one side and SiO<sub>2</sub> and/or Al<sub>2</sub>O<sub>3</sub> on the other side. The quantity of these compounds is however governed by the  
20 chemical composition of the green pellets which is itself controlled by the composition of the compounds initially used for producing them.

Metallic fluxed pellets have to fulfill critical criteria to be used in metallurgical reactors, such as blast furnace or direct reduction reactor. The mechanical and metallurgical properties of the fired pellets need to be  
25 adequate, for example, for avoiding decrepitation or swelling at high temperatures inside the metallurgical reactor.

The *green* (crude) pellets also have to present adequate physical properties to resist to the hardening process without being degraded by the increase of the temperature and the compression  
30 constraints into the induration furnace.

In addition to this, it is important to control the moisture of the green fluxed pellets. The ratio between the solid components and the water added during the balling process is crucial for having pellets with the right size, as well as presenting a good behavior in the next steps of the process, especially inside the induration furnace. The ratio between the different components in the starting powdered composition are therefore crucial for processing green pellets presenting the appropriate physicochemical properties during the induration process as well as later on in the form of fired pellets, inside the metallurgical reactors.

Moreover, actually, notably due to the impoverishment of metallic ore, it is also quite often required being able to process green pellets starting from metallic concentrate in the form of a slurry (i.e. a suspension, in particular an aqueous suspension) of metallic concentrate. The control of the moisture content during the balling process is therefore in this case much more challenging.

On the other hand, the resulting *fired* pellets have also to present satisfactory physical and metallurgical properties to be used afterwards in metallurgical reactors.

The physical properties are essential for example because breakage and abrasion of the fired pellets lead to the loss of material during their storage and transportation. Moreover, it is preferable for the fired pellets to present a good mechanical strength, also called crushing or compressive strength, in order to avoid any loss of permeability in the metallurgical reactor when charged into it. The mechanical strength of the pellets can be measured, for example by the ISO standard 4700, "Determination of the crushing strength".

The metallurgical qualities of the fired pellets are also an important criterion which is characterized by the reducibility, the swelling and the low temperature breakdown of the fired pellets, notably according to the ISO standard 7215, "Determination of the reducibility by the final degree of reduction index" or according to standard ISO 4695

“Determination of the reducibility by the rate of reduction index”, the ISO standard 4698, “Determination of the free-swelling index” and the ISO standard 4696 “Determination of low-temperature reduction-disintegration indices by static method”.

5 Document J. Pan et al. which has been cited previously (see Iron Ore conference / Perth, WA, 11-13 July 2011, J Pan, D Q Zhu, M Emrich, T J Chun and H Chen, “Improving the fluxed pellets performance by hydrated lime instead of bentonite as binder” also mentions that in producing fluxed pellets, MgO content significantly affects the firing  
10 performance of fluxed pellets and higher MgO content leads to a lower compressive strength of the fired pellets made from preheated pellets (see Zhang, 2009 and Wang, Liu and Chen, 2004).

Although, it has been found that 0.9 % pure MgO in pellet can reduce the reduction degradation index (RDI) to as low as 7.5 %, it  
15 also shows a deterioration in compressive strength of the fired pellets (see Transactions of the Indian Institute of Metals, August 2016, Volume 69, Issue 6, pp 1141–1153, Role of MgO and Its Different Minerals on Properties of Iron Ore Pellet, Md. Meraj, Susanta Pramanik, Jagannath Pal.). This document states that when adding magnesium additives, the  
20 strength of the fired pellets will be decreased because of the oxidation of magnetite which is delayed by the presence of MgO in the pellets.

Other fluxes based on MgO have been tested and provide good strength properties at lower induration temperature but cannot reduce degradation index to sufficiently low level.

25 In view of these sensitive requirements, it is not easy to modify the composition of metallic ore fluxed pellets without completely disrupting the sensible physicochemical properties of the green and the fired pellets. Because the quality of the fired pellets depends on the properties of the green pellets, it is also necessary to control the quality of  
30 the green pellets for obtaining adequate fired pellets suitable for use in metallurgical furnaces.



Despite its drawbacks, bentonite is at the moment recommended to achieve all the above mentioned requirements essential to obtain adequate metallic fluxed pellets suitable for withstanding an induration process when in the form of green pellets and thereafter for use  
5 in direct reduction reactors or blast furnaces when in the form of fired pellets.

However, there is still a need to provide alternative metallic ore fluxed pellets, in particular iron ore fluxed pellets presenting controlled basicity, controlled moisture and enhanced mechanical and metallurgical  
10 properties while reducing the volume of slag in the metallurgical furnace.

To this end, the invention provides the use of a magnesium-including compound as binder for producing metallic ore fluxed pellets, in particular iron ore fluxed pellets characterized in that the magnesium-including compound comprises semi-hydrated dolime or dolomitic lime  
15 fitting the general formula  $a\text{Ca}(\text{OH})_2 \cdot b\text{Mg}(\text{OH})_2 \cdot c\text{MgO}$ , a, b, and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime.

This compound is a dolomite or dolomitic limestone  
20 derivative, which will be called a semi-hydrated dolime in the present invention, obtained by calcination and then by partial hydration (slaking with water) of a natural dolomite or dolomitic limestone.

The semi-hydrated dolime may therefore contain the same impurities than those of the dolomite from which it is produced.

25 Semi-hydrated dolime according to the present invention may so contain impurities, such as sulphur oxide,  $\text{SO}_3$ , silica,  $\text{SiO}_2$  or even alumina,  $\text{Al}_2\text{O}_3$ , the sum of which being at a level of some weight %. The impurities are expressed herein under their oxide form, but of course, they might appear as different minerals. Semi-hydrated dolime contains  
30 generally also some weight % (up to 10%) of residual unburned residues, namely magnesium and/or calcium carbonates,  $\text{MgCO}_3$  and/or  $\text{CaCO}_3$

(usually essentially  $\text{CaCO}_3$ ). In some cases, some unreacted (not slaked) calcium oxide  $\text{CaO}$  might appear at a level of 1% by weight or less.

As may be seen, the present invention describes the use not of physical mixtures but actually of a single compound providing both  
5 magnesium and calcium compounds, namely  $\text{Mg}(\text{OH})_2$ ,  $\text{Ca}(\text{OH})_2$  and  $\text{MgO}$ . The use of a single compound instead of physical mixtures of multiple compounds has a considerable practical advantage, since the method for producing the pellets will be easier when a single binder is used instead of several ones. Further, the homogeneity of the dispersion of the  
10 Ca and Mg compounds in the composition of the pellets is also improved when both of these components are provided via a single binder, itself perfectly homogenous.

On the other hand, it has the advantage, as compared with completely hydrated dolomite, of being a product which is much easier to  
15 obtain. Indeed, totally hydrated dolomite, which may be represented by a weight formula of the type  $x\text{Ca}(\text{OH})_2.y\text{Mg}(\text{OH})_2$  and containing non-hydrated residues  $\text{CaO}$  and/or  $\text{MgO}$  only in trace amounts (less than 1%) is difficult to obtain, since it requires complete hydration of calcined dolomite, generally carried out under pressure up to 1 MPa (10 bars) and  
20 high temperature, up to  $180^\circ\text{C}$ . The totally hydrated dolomite of general formula  $x\text{Ca}(\text{OH})_2.y\text{Mg}(\text{OH})_2$  therefore remains at the present time a specialty product.

In the present invention, semi-hydrated dolime is used as a binder in order to let the metallic ore fluxed pellets to be formed properly  
25 and to withstand the induration process, giving afterwards fired pellets of good quality, meaning having good mechanical and metallurgical properties.

Indeed, it has been surprisingly observed in the present invention that it is possible to replace the commonly used binder, namely  
30 bentonite, by a binder composed of semi-hydrated dolime containing between 0.5 and 19.5 % by weight of  $\text{Mg}(\text{OH})_2$  without degrading the

physicochemical properties of the metallic ore fluxed pellets, against all expectations.

In the semi-hydrated dolime used as binder in the present invention, the proportion of  $\text{Mg}(\text{OH})_2$  is maintained between 0.5 and  
5 19.5 % by weight in order to control the moisture content of the composition during the process of production of green pellets and to enhance the mechanical properties of the resulting green pellets.

Advantageously, the weight fraction  $b$  of  $\text{Mg}(\text{OH})_2$  is higher than or equal to 1%, in particular higher than or equal to 1.5%, most  
10 particularly higher than or equal to 2%, preferably higher or equal to 5% and lower than or equal to 18%, in particular lower than or equal to 15 % by weight with respect to the total weight of said semi-hydrated dolime.

It has been demonstrated in the present invention that it is possible to fully replace bentonite or any organic product as a binder and  
15 olivine (or other silicate) as a flux with semi-hydrated dolime.

Another advantage of the use of semi-hydrated dolime as a binder leads to a decrease in the consumption of carbonates as a flux, if they are used, causing a decrease in the  $\text{CO}_2$  emissions during the induration process.

20 Moreover, when the semi-hydrated dolime according to the present invention is replacing silicates-including compounds, it allows the reduction of the slag-rate in the blast-furnace.

Preferably, according to the present invention, the weight ratio of said binder is between 0.5 % and 5 %, preferably between 0.5 %  
25 and 1.5 % by weight with respect to the total weight of the pellets.

Alternatively, according to the present invention, the weight fraction of semi-hydrated dolime is between 80 % and 100 %, preferably between 90 % and 100 %, more preferably between 95 % and 100 %, advantageously between 97 % and 100 %, preferably between 98 % and  
30 100 % by weight with respect to the total weight of the binder. In a

particular embodiment of the invention, the semi-hydrated dolime is 100% by weight with respect to the total weight of the binder.

Advantageously, the weight fraction  $c$  of MgO is greater than or equal to 5%, preferably greater than or equal to 10%, advantageously  
5 greater than or equal to 15%, preferentially greater than or equal to 20% by weight of MgO with respect to the total weight of said semi-hydrated dolime and is less than or equal to 41%, preferably less than or equal to 30% by weight of MgO with respect to the total weight of said semi-hydrated dolime.

10 In this particular embodiment of the invention, if higher MgO contents are envisaged, magnesium oxide can be added as a complementary flux. More preferably, the weight fraction  $a$  of  $\text{Ca}(\text{OH})_2$  is greater than or equal to 15%, preferably greater than or equal to 30%, advantageously greater than or equal to 40%, preferentially greater than or  
15 equal to 45% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime and is less than or equal to 85%, preferably less than or equal to 65%, advantageously less than or equal to 60%, more preferably less than or equal to 55% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime.

20 Preferably, the semi-hydrated dolime is in a powdery form.

Alternatively, the semi-hydrated dolime is in the form of an aqueous suspension of said compound based on said semi-hydrated dolime.

Moreover, in a particular embodiment, the semi-hydrated  
25 dolime comprises particles presenting BET specific surface area obtained from nitrogen adsorption comprised between 5 and 25  $\text{m}^2/\text{g}$ , in particular between 10  $\text{m}^2/\text{g}$  and 20  $\text{m}^2/\text{g}$ .

By the term "particles" in the sense of the present invention, it is meant the smallest solid discontinuity of the mineral filler which may be  
30 observed with a scanning electron microscope (SEM).

By the expression "BET specific surface area", it is meant in the meaning of the present specification the specific surface area measured by manometry with adsorption of nitrogen at 77 K after degassing under vacuum at a temperature comprised between 150 and 5 250°C, notably at 190°C for at least 2 hours and calculated according to the multipoint BET method as described in the ISO 9277:2010E standard.

Advantageously, the semi-hydrated dolime comprises particles presenting a total BJH pore volume consisting of pores with a diameter lower than 1000 Å, obtained from nitrogen desorption comprised 10 between 0.05 and 0.15 cm<sup>3</sup>/g.

By the terms "BJH pore volume" according to the present invention, it is meant the pore volume as measured by manometry with adsorption of nitrogen at 77 K after degassing under vacuum at a temperature comprised between 150 and 250°C, notably at 190°C for at 15 least 2 hours and calculated according to the BJH method, using the desorption curve, with the hypothesis of a cylindrical pore geometry.

By the terms "total pore volume" in the present specification, it is meant the BJH pore volume consisting of pores with a diameter smaller than or equal to 1000 Å.

20 Preferably, the semi-hydrated dolime comprises particles presenting a  $d_{10}$  greater or equal to 0.5 μm, in particular about 1 μm.

Moreover, the semi-hydrated dolime comprises advantageously particles presenting a  $d_{50}$  comprised between 4 μm and 8 μm.

25 In particular, the semi-hydrated dolime comprises particles presenting a  $d_{97}$  comprised between 40 μm and 95 μm.

The notation  $d_x$  represents a diameter expressed in μm, measured by laser granulometry in methanol after sonication, relatively to which X % by volume of the measured particles are smaller or equal.

30 In another embodiment of the present invention, the metallic ore fluxed pellets, in particular iron ore fluxed pellets, contain metallic ore

concentrate, in particular iron ore concentrate, presenting particles having a Blaine fineness comprised between 1500 cm<sup>2</sup>/g and 2500 cm<sup>2</sup>/g, preferably between 1800 cm<sup>2</sup>/g and 2200 cm<sup>2</sup>/g.

By the expression "Blaine fineness", it is meant in the meaning of the present specification fineness measured according to the  
5 ASTM standard C-204-07 using an air-permeability apparatus and the Test Method A. The Blaine fineness of particles is the specific surface area expressed as the surface area in square centimetres per gram of particles.

In a particularly preferred embodiment according to the invention, the metallic ore fluxed pellets, in particular iron ore fluxed pellets,  
10 present a size distribution characterized by 90% to 98 % of the pellets presenting a diameter comprised between 8 to 16 mm.

In a particularly preferred embodiment according to the invention, metallic ore fluxed pellets are iron ore fluxed pellets comprising  
15 fine iron ore concentrate selected from the group consisting of magnetite, hematite and mixture thereof.

In another embodiment of the present invention, the metallic ore fluxed pellets, in particular the iron ore fluxed pellets further comprise a flux selected from the group consisting of calcium carbonate, dolomite,  
20 olivine, pyroxenite, other magnesium silicates, like dunite, and mixture thereof.

Preferably, said flux is between 0.5 % and 15 % by weight with respect to the total weight of the pellets.

Advantageously, according to the present invention, the metallic ore fluxed pellets, in particular the iron ore fluxed pellets are crude  
25 metallic ore fluxed pellets, in particular crude iron ore fluxed pellets.

The moisture content of the pellets is controlled, even in the absence of bentonite, and the mechanical and metallurgical properties of the pellets are enhanced.

30 The crude metallic ore fluxed pellets are characterized by a crushing strength before drying ("wet pellet") which is comprised between

10 and 30 N per pellet and after drying ("dried pellet") which is comprised between 30 and 90 N per pellet .

The crude metallic ore fluxed pellets according to the present invention present a shock temperature equal to or more than 250 °C.

5 By the terms "shock temperature" it is meant according to the present invention the minimum temperature at which cracks are produced in the wet crude pellets when put inside a hot muffle, directly from room temperature. To this purpose, various samples of crude pellets are submitted individually to gradually increased temperature. Typically, a first  
10 sample will be subject to 200°C, a second to 250°C..., until cracked pellets are observed in one sample. Those cracks appear very quickly ( a few minutes) in the pellets after submission to the setting temperature.

Alternatively, the metallic ore fluxed pellets, in particular the iron ore fluxed pellets according to the present invention are fired metallic  
15 ore fluxed pellets, in particular fired iron ore fluxed pellets.

Thanks to the semi-hydrated dolime used as binder in the present invention, the fired pellets presents also enhanced mechanical properties after the hardening process. The crushing strength of the fired pellets according to the present invention measured according to standard  
20 ISO 4700 is comprised between 2000 and 5000 N/pellet, preferably comprised between 2500 and 5000 N/pellet.

Moreover, the quality of the fired pellets according to the present invention has been enhanced since the replacement of the minerals contained in the bentonite allows for example the reduction of the  
25 volume of slag in the blast-furnace or electric arc furnace after the direct reduction reactor.

Preferably, the fired pellets according to the invention contain less than 10 %, in particular less than 5% by weight of SiO<sub>2</sub> with respect to the total weight of the pellets.

30 The total metal, in particular iron, content in the fired pellets is preferably equal to or higher than 55 %, in particular equal to or higher

than 60%, advantageously equal to or higher than 65% by weight with respect to the total weight of the pellets.

The metallurgical properties of the fired pellets obtained according to the present invention are a reducibility above 0.70 %/minute, following the standard ISO 4695, "Determination of the reducibility by the rate of reduction index", below 20% swelling (by buoyancy), following the standard ISO 4698, "Determination of the free-swelling index" and a crushing strength after reduction above 150 N/pellet, following the standard ISO 4696 "Determination of low-temperature reduction-disintegration indices by static method». The use of semi-hydrated dolime containing magnesium hydroxide in a proportion comprised between 0.5 and 19.5 % by weight as binder in metallic ore fluxed pellets allows therefore the production of metallic ore fluxed pellets with adequate mechanical properties together with an adequate chemical composition for use in electrical or blast furnace.

Other embodiments of the use according to the invention are mentioned in the annexed claims.

The invention relates also to a process for manufacturing metallic ore fluxed pellets, in particular iron ore fluxed pellets comprising the steps of:

- feeding a fine metallic ore concentrate, in particular a iron ore concentrate in a container;
- feeding a binder in said container ;
- adjusting moisture in said container to form a wet mixture;
- balling and sieving said wet mixture into crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets;

characterized in that said binder is a magnesium-including compound comprising semi-hydrated dolime fitting the general formula  $a\text{Ca}(\text{OH})_2.b\text{Mg}(\text{OH})_2.c\text{MgO}$ , a, b and c being weight fractions wherein the



weight fraction  $b$  of  $Mg(OH)_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime.

The balling and the sieving step is preferably performed in a granulating vessel like a drum or disk (pan) which can be the container or  
5 not.

The residence time of the wet mixture to form the pellets inside the granulating drum is comprised between 50 and 200 s for pellets presenting a diameter comprised between 8 and 16 mm.

Preferably, the process according to the present invention  
10 further comprises the step of hardening the crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets in an induration furnace.

Said hardening step comprises advantageously the steps of: drying the crude pellets at about 300°C during a predetermined duration comprised between 5 min and 15 min for forming dried crude pellets;

- 15
- pre-heating the dried crude pellets at a temperature equal to or higher than 800°C during a predetermined duration comprised between 5 min and 20 min for forming pre-heated crude pellets;
  - firing the pre-heated crude pellets at a temperature equal  
20 to or higher than 1200°C during a predetermined duration comprised between 5 min and 20 min to form fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets;

Advantageously, according to the present invention, the step  
25 of adjusting moisture is a step of adding an aqueous phase to form said wet mixture.

The step of adding an aqueous phase is preferably a gradual addition of the aqueous phase into the powdered mixture.

Preferably the aqueous phase is water.

30 Advantageously, according to the invention, the step of adjusting moisture is performed until said mixture presents a moisture

content comprised between 5 % et 15% by weight with respect to the total weight of said mixture.

In another embodiment of the process according to the invention, crude metallic ore fluxed pellets, in particular crude iron ore  
5 fluxed pellets present a size distribution characterized by 90% to 98 % of the pellets presenting a diameter comprised between 8 to 16 mm.

Preferably, the process according to the invention further comprises a step of feeding a flux before the step of adjusting moisture, the flux being preferably selected from the group consisting of calcium  
10 carbonate, olivine, pyroxenite, other magnesium silicates and mixture thereof.

Preferably, the weight fraction  $c$  of MgO is greater than or equal to 5%, preferably greater than or equal to 10%, advantageously greater than or equal to 15%, preferentially greater than or equal to 20% by  
15 weight of MgO with respect to the total weight of said semi-hydrated dolime and is less than or equal to 41%, preferably less than or equal to 30% by weight of MgO with respect to the total weight of said semi-hydrated dolime, the weight fraction  $a$  of  $\text{Ca}(\text{OH})_2$  is greater than or equal to 15%, preferably greater than or equal to 30%, advantageously greater than or  
20 equal to 40%, preferentially greater than or equal to 45% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime and is less than or equal to 85%, preferably less than or equal to 65%, advantageously less than or equal to 60%, more preferably less than or  
25 equal to 55% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime.

Advantageously, in the process according to the invention, the binder is added in a quantity comprised between 0.5 % and 5 %, preferably between 0.5 % and 1.5 % by weight with respect to the total weight of the pellets.

30 Alternatively, according to the present invention, the weight fraction of semi-hydrated dolime is between 80 % and 100 %, preferably

between 90 % and 100 %, more preferably between 95 % and 100 %, advantageously between 97 % and 100 %, preferably between 98 % and 100 % by weight with respect to the total weight of the binder. In a particular embodiment of the invention, the semi-hydrated dolime is 100% by weight with respect to the total weight of the binder.

In the process according to the invention, said fine metallic ore concentrate, in particular iron ore concentrate presents advantageously a Blaine fineness comprised between 1500 cm<sup>2</sup>/g and 2500 cm<sup>2</sup>/g, preferably between 1800 cm<sup>2</sup>/g and 2200 cm<sup>2</sup>/g.

Other embodiments of the process according to the invention are mentioned in the annexed claims.

The present invention relates also to a metallic ore fluxed pellets, in particular iron ore fluxed pellets composition comprising:

- a fine metallic ore concentrate, in particular an iron ore concentrate in a quantity comprised between 80 weight % and 99 weight % with respect to the total weight of the metallic ore fluxed pellets composition;
- a magnesium-including compound as binder in a quantity comprised between 0.1 weight % and 5 weight %, in particular between 0.5 weight % and 1.5 weight % with respect to the total weight of the metallic ore fluxed pellets composition;
- a moisture content comprised between 5 weight % and 15 weight % with respect to the total weight of the metallic ore fluxed pellets composition;

characterized in that the magnesium-including compound comprises a semi-hydrated dolime fitting the general formula  $a\text{Ca}(\text{OH})_2 \cdot b\text{Mg}(\text{OH})_2 \cdot c\text{MgO}$ , a, b, and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime.

Alternatively, according to the present invention, the weight fraction of semi-hydrated dolime is between 80 % and 100 %, preferably between 90 % and 100 %, more preferably between 95 % and 100 %, advantageously between 97 % and 100 %, preferably between 98 % and  
5 100 % by weight with respect to the total weight of the binder. In a particular embodiment of the invention, the semi-hydrated dolime is 100%by weight with respect to the total weight of the binder.

Advantageously, the composition according to the invention further comprises from 0.5 weight% to 15 weight % of additives as fluxes  
10 with respect to the total weight of the metallic ore fluxed pellets composition.

Preferably, in the composition according to the invention, the weight fraction  $c$  of MgO is greater than or equal to 5%, preferably greater than or equal to 10%, advantageously greater than or equal to 15%,  
15 preferentially greater than or equal to 20% by weight of MgO with respect to the total weight of said semi-hydrated dolime and is less than or equal to 41%, preferably less than or equal to 30% by weight of MgO with respect to the total weight of said semi-hydrated dolime, the weight fraction  $a$  of  $\text{Ca}(\text{OH})_2$  is greater than or equal to 15%, preferably greater than or equal  
20 to 30%, advantageously greater than or equal to 40%, preferentially greater than or equal to 45% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime and is less than or equal to 85%, preferably less than or equal to 65%, advantageously less than or equal to 60%, more preferably less than or equal to 55% by weight of  $\text{Ca}(\text{OH})_2$  with  
25 respect to the total weight of said semi-hydrated dolime.

In another embodiment of the composition according to the invention, the semi-hydrated dolime comprises particles presenting BET specific surface area obtained from nitrogen adsorption comprised between 5 and 25  $\text{m}^2/\text{g}$ , preferably between 10  $\text{m}^2/\text{g}$  and 20  $\text{m}^2/\text{g}$ .

30 Preferably, the semi-hydrated dolime of the composition according to the invention comprises particles presenting a total BJH pore

volume consisting of pores with a diameter lower than 1000 Å, obtained from nitrogen desorption comprised between 0.05 and 0.15 cm<sup>3</sup>/g.

More preferably, the semi-hydrated dolime comprises particles presenting a size characterized either by a d<sub>10</sub> equal to or greater than 0.5 μm, and/or a d<sub>50</sub> comprised between 4 μm and 8 μm, and/or a d<sub>97</sub> comprised between 40 μm and 95 μm.

Alternatively, the metallic ore concentrate, in particular iron ore concentrate presents particles having a Blaine fineness comprised between 1500 cm<sup>2</sup>/g and 2500 cm<sup>2</sup>/g, preferably between 1800 cm<sup>2</sup>/g and 2200 cm<sup>2</sup>/g.

Preferably, the fine iron ore concentrate is selected from the group consisting of magnetite, hematite and mixture thereof.

In a preferred embodiment, the composition according to the invention, further comprises a flux selected from the group consisting of calcium carbonate, dolomite, olivine, pyroxenite, other magnesium silicates, like dunite, and mixture thereof.

Other embodiments of the metallic ore fluxed pellets, in particular iron ore fluxed pellets composition according to the invention are mentioned in the annexed claims.

The present invention relates also to crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets comprising:

- a fine metallic ore concentrate, in particular an iron ore concentrate in a quantity comprised between 80 weight % and 99 weight % with respect to the total weight of the crude metallic ore fluxed pellets;
- a magnesium-including compound as binder in a quantity comprised between 0.1 weight % and 5 weight %, in particular between 0.5 weight % and 1.5 weight % with respect to the total weight of the crude metallic ore fluxed pellets;

- a moisture content comprised between 5 weight % and 15 weight % with respect to the total weight of the crude metallic ore fluxed pellets ;

characterized in that the magnesium-including compound comprises a semi-hydrated dolime fitting the general formula  $a\text{Ca}(\text{OH})_2.b\text{Mg}(\text{OH})_2.c\text{MgO}$ , a, b, and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime, said crude metallic ore fluxed pellets.

Alternatively, according to the present invention, the weight fraction of semi-hydrated dolime is between 80 % and 100 %, preferably between 90 % and 100 %, more preferably between 95 % and 100 %, advantageously between 97 % and 100 %, preferably between 98 % and 100 % by weight with respect to the total weight of the binder. In a particular embodiment of the invention, the semi-hydrated dolime is 100%by weight with respect to the total weight of the binder.

In particular said crude iron ore fluxed pellets further presenting a crushing strength comprised between 10 and 30 N/pellet.

Advantageously, the crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets further comprises from 0.5 weight% to 15 weight % of additives as fluxes with respect to the total weight of the crude metallic ore fluxed pellets.

Alternatively, according to the present invention, the crude metallic ore fluxed pellets, in particular the crude iron ore fluxed pellets present a shock temperature equal to or higher than 250 °C.

Preferably, said crude metallic ore fluxed pellets, in particular said crude iron ore fluxed pellets further present a crushing strength between 30 and 90 N/ pellet after drying.

This means that the crude pellets present a crushing strength comprised between 10 and 30 N/pellet before drying, when they are crude

wet pellets, and present a crushing strength between 30 and 90 N/pellet after drying, when they are crude dried pellets.

The drying step is performed at about 105°C during a predetermined duration typically comprised between 12 h and 24h.

5                    Advantageously, the crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to the invention present a size distribution wherein 90% to 98 % of the pellets presents a diameter comprised between 8 to 16 mm.

10                    The crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to the invention comprise advantageously fine iron ore concentrate selected from the group consisting of magnetite, hematite and mixture thereof.

15                    Preferably, the crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to the invention further comprise a flux selected from the group consisting of calcium carbonate, dolomite, olivine, pyroxenite, other magnesium silicates, like dunite, and mixture thereof.

20                    Advantageously, the crude pellets according to the invention contain metallic ore concentrate, in particular iron ore concentrate presenting particles having a Blaine fineness comprised between 1500 cm<sup>2</sup>/g and 2500 cm<sup>2</sup>/g, preferably between 1800 cm<sup>2</sup>/g and 2200 cm<sup>2</sup>/g.

Other embodiments of crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to the invention are mentioned in the annexed claims.

25                    The present invention relates also to fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets comprising:

30                    - a metal content equal to or higher than 55 %, in particular equal to or higher than 60%, advantageously equal to or higher than 65% by weight with respect to the total weight of the pellets, characterized in that the pellets present a Ca/Mg ratio between 0.8 and 2, in particular between 0.8 and 1.7, most particularly between 0.8 and 1.2

and present a crushing strength measured according to standard ISO 4700 comprised between 2000 and 5000 N/pellet, preferably comprised between 2500 and 5000 N/pellet.

5 In another embodiment of the fired pellets according to the invention, said fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets contain less than 10 %, in particular less than 5% by weight of SiO<sub>2</sub> with respect to the total weight of the pellets.

The fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets according to the invention comprise advantageously fine iron  
10 ore concentrate selected from the group consisting of magnetite, hematite and mixture thereof.

Preferably, the fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets according to the invention further comprise a flux selected from the group consisting of calcium carbonate, dolomite,  
15 olivine, pyroxenite, other magnesium silicates, like dunite, and mixture thereof.

In a particularly preferred embodiment according to the invention, the fired metallic iron ore fluxed pellets, in particular fired iron ore fluxed pellets present a size distribution wherein 90% to 98 % of the pellets  
20 presents a diameter comprised between 8 to 16 mm.

Other embodiments of fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets according to the invention are mentioned in the annexed claims.

#### Example

25 A composition containing the binder according to the invention has been implemented and present the characteristics presented in table 1. In table 1, the weight % are expressed with respect to the total weight of the pellets.



Table1

Basicity expressed as (CaO/SiO <sub>2</sub> )	0.75
Mg expressed as MgO (weight %)	1.3
Magnetite (weight %)	57.4
Hematite (weight %)	36.6
Limestone (weight %)	1.2
Dolomite (weight %)	2.8
Semi-hydrated dolime (weight %)	1.5
Bentonite (weight %)	0
Anthracite (weight %)	0.5

The amount of elemental Mg expressed as MgO represents the amount of elemental Mg in the mixture of the different components forming the composition of the pellets.

Limestone and dolomite appear as fluxes. Water is added to composition according to table 1 in order to ball and sieve the resulting wet mixture into crude pellets.

The crude pellets are dried at about 300°C for forming dried crude pellets. The dried crude pellets are pre-heated at 800°C for forming pre-heated crude pellets. The pre-heated crude pellets are fired at 1280°C to form fired pellets. The total cycle time from the drying step to the end of the firing step is 22.4 minutes and the bed height green balls/hearth layer is 300/100 mm.

The fired pellets present 64.2 weight % of Fe and 4.2 weight % of SiO<sub>2</sub> based on the total weight of the fired pellets.

The crushing strength of the fired pellets measured according to the standard ISO 4700 is 3320 N/pellet.

The fired pellets are subjected to a swelling test according to standard ISO 4698 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

Then, the fired pellets are subjected to a reducibility test according to standard ISO 4695 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

Finally, the fired pellets are subjected to a desintegration test according to standard ISO 4696 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

The results of these measurements are shown in table 2.

5

Table 2

Crushing strength according to ISO 4700 on pellets after swelling test according ISO 4698 (N/pellet)	180
Crushing strength according to ISO 4700 on pellets after reducibility test according ISO 4695 (N/pellet)	420
Crushing strength according to ISO 4700 on pellets after desintegration test according ISO 4696 (N/pellet)	260

A composition containing a binder according to the invention has been implemented and presents the characteristics presented in table 3. In table 3, the weight % are expressed with respect to the total weight of the pellets.

10

**Table 3**

Basicity expressed as (CaO/SiO <sub>2</sub> )	0.2
Mg expressed as MgO (weight %)	1.22
Magnetite (weight %)	49.5
Hematite (weight %)	49.5
Binder comprising semi hydrated dolime (weight %)	1

The amount of elemental Mg expressed as MgO represents the amount of elemental Mg in the mixture of the different components forming the composition of the pellets.

15

The composition above comprises 0.6 weight % of coke and 1.52 weight % of olivine both expressed with respect to the sum of the weight of hematite and magnetite.

The binder composition comprising semi hydrated dolime is presented in table 4, wherein the weight % are expressed with respect to the total weight of the binder.

**Table 4**

Mg(OH) <sub>2</sub> (weight %)	1.24
Ca(OH) <sub>2</sub> (weight %)	57.41
CaCO <sub>3</sub> (weight %)	2.84
CaO (weight %)	4.2
MgO (weight %)	33.1
Fe <sub>2</sub> O <sub>3</sub> (weight %)	0.42
Other impurities (weight %)	0.79

5

Water is added to the composition in order to ball and sieve the resulting wet mixture into crude pellets.

The crude pellets are dried at about 300°C for forming dried crude pellets. The dried crude pellets are pre-heated at 800°C for forming pre-heated crude pellets. The pre-heated crude pellets are fired at 1270°C to form fired pellets. The total cycle time from the drying step to the end of the firing step is 27.4 min and the bed height green balls/hearth layer is 300/100 mm.

The fired pellets presents 66 weight % of Fe and 2.95 weight % of SiO<sub>2</sub> based on the total weight of the fired pellets.

The crushing strength of the fired pellets measured according to the standard ISO 4700 is 2920 N/pellet.

The fired pellets are subjected to a swelling test according to standard ISO 4698 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

The fired pellets are subjected to a reducibility test according to standard ISO 4695 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

Finally the fired pellets are subjected to a disintegration test according to standard ISO 4696 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

The results of these measurements are shown in table 5.

5 **Table 5**

Crushing strength according to ISO 4700 on pellets after swelling test according ISO 4698 (N/pellet)	300
Crushing strength according to ISO 4700 on pellets after reducibility test according ISO 4695 (N/pellet)	310
Crushing strength according to ISO 4700 on pellets after disintegration test according ISO 4696 (N/pellet)	210

#### Comparative example

A composition containing bentonite as binder has been implemented and present the characteristics presented in table 6. In table 10 6, the weight % are expressed with respect to the total weight of the pellets.

Table 6

Basicity expressed as (CaO/SiO <sub>2</sub> )	0.75
Mg, expressed as MgO (weight %)	1.3
Magnetite (weight %)	56.1
Hematite (weight %)	36.3
Limestone (weight %)	1.8
Dolomite (weight %)	4.7
Semi-hydrated dolime (weight %)	0
Bentonite (weight %)	0.6
Anthracite (weight %)	0.5

The amount of elemental Mg expressed as MgO represents the amount of elemental Mg in the mixture of the different components forming the composition of the pellets.

5 Limestone and dolomite appear as fluxes. Water is added to composition according to table 6 in order to ball and sieve the resulting wet mixture into crude pellets.

The crude pellets are dried at about 300°C for forming dried crude pellets. The dried crude pellets are pre-heated at 800°C for forming pre-heated crude pellets. The pre-heated crude pellets are fired at 1280°C  
10 to form fired pellets. The total cycle time from the drying step to the end of the firing step is 22.4 minutes and the bed height green balls/hearth layer is 300/100 mm.

The fired pellets present 63.7 weight % of Fe and 3.5 weight % of SiO<sub>2</sub> based on the total weight of the fired pellets.

15 The crushing strength of the fired pellets measured according to the standard ISO 4700 is 2410 N/pellet.

The fired pellets are subjected to a swelling test according to standard ISO 4698 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

20 Then, the fired pellets are subjected to a reducibility test according to standard ISO 4695 and afterwards the crushing strength of the pellets is measured according to the standard ISO 4700.

Finally, the fired pellets are subjected to a desintegration test according to standard ISO 4696 and afterwards the crushing strength of the pellets is  
25 measured according to the standard ISO 4700.

The results of these measurements are shown in table 7.

Table 7

Crushing strength according to ISO 4700 on pellets after swelling test according ISO 4698 (N/pellet)	110
Crushing strength according to ISO 4700 on pellets after reducibility test according ISO 4695 (N/pellet)	260
Crushing strength according to ISO 4700 on pellets after desintegration test according ISO 4696 (N/pellet)	150

As it can be seen from tables 2, 5 and 7, the crushing strengths of the fired pellets made from the composition according to the present invention are well above the one of the pellets containing bentonite as binder.

CLAIMS

1. Use of a magnesium-including compound as binder for producing metallic ore fluxed pellets, in particular iron ore fluxed pellets characterized in that the magnesium-including compound comprises semi-hydrated dolime fitting the general formula  $a\text{Ca}(\text{OH})_2.b\text{Mg}(\text{OH})_2.c\text{MgO}$ , a, b, and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime.
2. Use according to claim 1 wherein the weight fraction of said binder is between 0.5 % and 5 %, preferably between 0.5 % and 1.5 % by weight with respect to the total weight of the pellets.
3. Use according to claim 1 or claim 2 wherein the weight fraction of semi-hydrated dolime is between 70 % and 100 %, preferably between 75 % and 100 %, more preferably between 80 % and 100 %, advantageously between 85 % and 100 %, preferably between 90 % and 100 % by weight with respect to the total weight of the binder.
4. Use according to any one of claims 1 to 3, wherein the weight fraction c of MgO is greater than or equal to 5%, preferably greater than or equal to 10%, advantageously greater than or equal to 15%, preferentially greater than or equal to 20% by weight of MgO with respect to the total weight of said semi-hydrated dolime and is less than or equal to 41%, preferably less than or equal to 30% by weight of MgO with respect to the total weight of said semi-hydrated dolime.
5. Use according to any one of claims 1 to 4, wherein the weight fraction a of  $\text{Ca}(\text{OH})_2$  is greater than or equal to 15%, preferably greater than or equal to 30%, advantageously greater than or equal to 40%, preferentially greater than or equal to 45% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime and is less than or equal to 85%, preferably less than or equal to 65%, advantageously less than or equal to 60%, more preferably less than or

equal to 55% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime.

6. Use according to any one of claims 1 to 5 wherein the semi-hydrated dolime is in a powdery form.

5 7. Use according to any one of claims 1 to 5 wherein the semi-hydrated dolime is in the form of an aqueous suspension of said semi-hydrated dolime.

8. Use according to any one of claims 1 to 7 wherein the semi-hydrated dolime comprises particles presenting BET specific surface area obtained from nitrogen adsorption comprised between 5 and 25  $\text{m}^2/\text{g}$ , preferably between 10  $\text{m}^2/\text{g}$  and 20  $\text{m}^2/\text{g}$ .

10 9. Use according to any one of claims 1 to 8 wherein the semi-hydrated dolime comprises particles presenting a total BJH pore volume consisting of pores with a diameter lower than 1000 Å, obtained from nitrogen desorption comprised between 0.05 and 0.15  $\text{cm}^3/\text{g}$ .

10. Use according to any one of claims 1 to 9 wherein the semi-hydrated dolime comprises particles presenting a  $d_{10}$  greater or equal to 0.5  $\mu\text{m}$ .

20 11. Use according to any one of claims 1 to 10 wherein the semi-hydrated dolime comprises particles presenting a  $d_{50}$  comprised between 4  $\mu\text{m}$  and 8  $\mu\text{m}$ .

25 12. Use according to any one of claims 1 to 11 wherein the semi-hydrated dolime comprises particles presenting a  $d_{97}$  comprised between 40  $\mu\text{m}$  and 95  $\mu\text{m}$ .

30 13. Use according to any one of the preceding claims wherein the metallic ore fluxed pellets, in particular iron ore fluxed pellets contain metallic or concentrate, in particular iron ore concentrate presenting particles having a Blaine fineness comprised between 1500  $\text{cm}^2/\text{g}$  and 2500  $\text{cm}^2/\text{g}$ , preferably between 1800  $\text{cm}^2/\text{g}$  and 2200  $\text{cm}^2/\text{g}$ .



14. Use according to any one of the preceding claims, wherein the metallic ore fluxed pellets, in particular iron ore fluxed pellets present a size distribution wherein 90% to 98 % of the pellets presents a diameter comprised between 8 to 16 mm.

5           15. Use according to any one of the preceding claims wherein metallic ore fluxed pellets are iron ore fluxed pellets comprising fine iron ore concentrate selected from the group consisting of magnetite, hematite and mixture thereof.

10           16. Use according to any one of the preceding claims wherein the metallic ore fluxed pellets, in particular the iron ore fluxed pellets further comprise a flux selected from the group consisting of calcium carbonate, dolomite, olivine, pyroxenite, other magnesium silicates, like dunite, and mixture thereof.

15           17. Use according to any one of the preceding claims wherein the metallic ore fluxed pellets, in particular the iron ore fluxed pellets are crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets.

20           18. Use according to any one of the preceding claims 1 to 16 wherein the metallic ore fluxed pellets, in particular the iron ore fluxed pellets are fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets.

19. Process for manufacturing metallic ore fluxed pellets, in particular iron ore fluxed pellets comprising the steps of:

- 25
- feeding a fine metallic ore concentrate, in particular an iron ore concentrate in a container;
  - feeding a binder in said container;
  - adjusting moisture in said container to form a wet mixture;
  - balling and sieving said wet mixture into crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets;
- 30

characterized in that said binder is a magnesium-including compound comprising a semi-hydrated dolime fitting the general formula  $a\text{Ca}(\text{OH})_2.b\text{Mg}(\text{OH})_2.c\text{MgO}$ , a, b and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime.

20. Process according to claim 19, further comprising a firing step for hardening the crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets in an induration furnace.

21. Process according to claim 20 wherein said hardening step comprises the steps of :

- drying the crude metallic ore fluxed pellets at about 300°C during a predetermined period of time comprised between 5 min and 15 min for forming dried crude pellets;
- pre-heating the dried crude metallic ore fluxed pellets at a temperature equal to or higher than 800°C during a predetermined period of time comprised between 5 min and 20 min for forming pre-heated crude pellets;
- firing the pre-heated crude metallic ore fluxed pellets at a temperature equal to or higher than 1200°C during a predetermined duration comprised between 5 min and 20 min to form fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets;

22. Process according to any one of claims 19 to 21 wherein the step of adjusting moisture is a step of adding an aqueous phase to form said mixture.

23. Process according to any one of claims 19 to 22 wherein the step of adjusting moisture is performed until said mixture presents a moisture content comprised between 5 % et 15% by weight with respect to the total weight of said mixture.

24. Process according to any one of claims 19 to 23 wherein said crude metallic ore fluxed pellets, in particular crude iron ore

fluxed pellets present a size distribution wherein 90% to 98 % of the pellets presents a diameter comprised between 8 to 16 mm.

25. Process according to any one of claims 19 to 24 further comprising a step of feeding a flux before the step of adjusting  
5 moisture, the flux being preferably selected from the group consisting of calcium carbonate, olivine, pyroxenite, other magnesium silicates like dunite and mixture thereof.

26. Process according to any one of claims 19 to 25 wherein the weight fraction  $c$  of MgO is greater than or equal to 5%,  
10 preferably greater than or equal to 10%, advantageously greater than or equal to 15%, preferentially greater than or equal to 20% by weight of MgO with respect to the total weight of said semi-hydrated dolime and is less than or equal to 41%, preferably less than or equal to 30% by weight of MgO with respect to the total weight of said semi-hydrated dolime, the  
15 weight fraction  $a$  of  $\text{Ca}(\text{OH})_2$  is greater than or equal to 15%, preferably greater than or equal to 30%, advantageously greater than or equal to 40%, preferentially greater than or equal to 45% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime and is less than or equal to 85%, preferably less than or equal to 65%, advantageously less  
20 than or equal to 60%, more preferably less than or equal to 55% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime.

27. Process according to any one of claims 19 to 26 wherein the weight fraction of said binder is between 0.5 % and 5 %, preferably between 0.5 % and 1.5 % by weight with respect to the total  
25 weight of the pellets.

28. Process according to any one of claims 19 to 27 wherein said fine metallic ore concentrate, in particular iron ore concentrate present a Blaine fineness comprised between 1500  $\text{cm}^2/\text{g}$  and 2500  $\text{cm}^2/\text{g}$ , preferably between 1800  $\text{cm}^2/\text{g}$  and 2200  $\text{cm}^2/\text{g}$ .

30 29. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition comprising:

- a fine metallic ore concentrate, in particular an iron ore concentrate in a quantity comprised between 80 weight % and 99 weight % with respect to the total weight of the metallic ore fluxed pellets composition;
- 5 - a magnesium-including compound as binder in a quantity comprised between 0.1 weight % and 5 weight %, in particular between 0.5 weight % and 1.5 weight % with respect to the total weight of the metallic ore fluxed pellets composition;
- 10 - a moisture content comprised between 5 weight % and 15 weight % with respect to the total weight of the metallic ore fluxed pellets composition;

characterized in that the magnesium-including compound comprises a semi-hydrated dolime fitting the general formula  
15  $a\text{Ca}(\text{OH})_2.b\text{Mg}(\text{OH})_2.c\text{MgO}$ , a, b and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime.

30. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to claim 29 further comprising  
20 from 0.5 weight% to 15 weight % of additives as fluxes with respect to the total weight of the metallic ore fluxed pellets composition.

31. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to claim 29 or claim 30, wherein the weight fraction c of MgO is greater than or equal to 5%,  
25 preferably greater than or equal to 10%, advantageously greater than or equal to 15%, preferentially greater than or equal to 20% by weight of MgO with respect to the total weight of said semi-hydrated dolime and is less than or equal to 41%, preferably less than or equal to 30% by weight of MgO with respect to the total weight of said semi-hydrated dolime, the  
30 weight fraction a of  $\text{Ca}(\text{OH})_2$  is greater than or equal to 15%, preferably greater than or equal to 30%, advantageously greater than or equal to

40%, preferentially greater than or equal to 45% by weight of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime and is less than or equal to 85%, preferably less than or equal to 65%, advantageously less than or equal to 60%, more preferably less than or equal to 55% by weight  
5 of  $\text{Ca}(\text{OH})_2$  with respect to the total weight of said semi-hydrated dolime.

32. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to any one of claims 29 to 31, wherein the semi-hydrated dolime comprises particles presenting BET specific surface area obtained from nitrogen adsorption comprised  
10 between 5 and 25  $\text{m}^2/\text{g}$ , preferably between 10  $\text{m}^2/\text{g}$  and 20  $\text{m}^2/\text{g}$ .

33. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to any one of claims 29 to 32, wherein the semi-hydrated dolime comprises particles presenting a total BJH pore volume consisting of pores with a diameter lower than 1000 Å,  
15 obtained from nitrogen desorption comprised between 0.05 and 0.15  $\text{cm}^3/\text{g}$ .

34. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to any one of claims 29 to 33, wherein the semi-hydrated dolime comprises particles presenting a size  
20 characterized by a  $d_{10}$  greater or equal to 0.5  $\mu\text{m}$ , and/or a  $d_{50}$  comprised between 4  $\mu\text{m}$  and 8  $\mu\text{m}$ , and/or a  $d_{97}$  comprised between 40  $\mu\text{m}$  and 95  $\mu\text{m}$ .

35. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to any one of claims 29 to 34,  
25 wherein the metallic ore concentrate, in particular iron ore concentrate presents particles having a Blaine fineness comprised between 1500  $\text{cm}^2/\text{g}$  and 2500  $\text{cm}^2/\text{g}$ , preferably between 1800  $\text{cm}^2/\text{g}$  and 2200  $\text{cm}^2/\text{g}$ .

36. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to any one of claims 29 to 35,  
30 wherein the fine iron ore concentrate is selected from the group consisting of magnetite, hematite and mixture thereof.

37. Metallic ore fluxed pellets composition, in particular iron ore fluxed pellets composition according to any one of claims 29 to 36, further comprising a flux selected from the group consisting of calcium carbonate, dolomite, olivine, pyroxenite, other magnesium silicates, like  
5 dunite, and mixture thereof.

38. Crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets comprising

- 10 - a fine metallic ore concentrate, in particular an iron ore concentrate in a quantity comprised between 80 weight % and 99 weight % with respect to the total weight of the crude metallic ore fluxed pellets;
- 15 - a magnesium-including compound as binder in a quantity comprised between 0.1 weight % and 5 weight %, in particular between 0.5 weight % and 1.5 weight % with respect to the total weight of the crude metallic ore fluxed pellets;
- a moisture comprised between 5 weight % and 15 weight % with respect to the total weight of the crude metallic ore fluxed pellets;

20 characterized in that the magnesium-including compound comprises a semi-hydrated dolime fitting the general formula  $a\text{Ca}(\text{OH})_2 \cdot b\text{Mg}(\text{OH})_2 \cdot c\text{MgO}$ , a, b and c being weight fractions wherein the weight fraction b of  $\text{Mg}(\text{OH})_2$  is between 0.5 and 19.5 % by weight with respect to the total weight of said semi-hydrated dolime, .

25 39. Crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to claim 38 further comprising from 0.5 weight % to 15 weight % of additives as fluxes with respect to the total weight of the crude metallic ore fluxed pellets.

30 40. Crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to claim 38 or claim 39, wherein said

crude metallic ore fluxed pellets, in particular said crude iron ore fluxed pellets further present a shock temperature equal to or higher than 250 °C.

41. Crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to any one of claims 38 to 40, wherein  
5 said crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets present a size distribution wherein 90% to 98 % of the pellets presents a diameter comprised between 8 to 16 mm.

42. Crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to any one of claims 38 to 41, wherein  
10 the crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets comprise fine iron ore concentrate selected from the group consisting of magnetite, hematite and mixture thereof.

43. Crude metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to any one of claims 38 to 42, further  
15 comprising a flux selected from the group consisting of calcium carbonate, dolomite, olivine, pyroxenite, other magnesium silicates, like dunite, and mixture thereof.

44. Fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets comprising:  
20 - a metal content equal to or higher than 55 %, in particular equal to or higher than 60%, advantageously equal to or higher than 65% weight with respect to the total weight of the pellets;

characterized in that the pellets present a Ca/Mg ratio between 0.8 and 2,  
25 in particular between 0.8 and 1.7, most particularly between 0.8 and 1.2 and present a crushing strength measured according to standard ISO 4700 comprised between 2000 and 5000 N/pellet, preferably comprised between 2500 and 5000 N/ pellet.

45. Fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets according to claim 44, wherein said fired metallic ore  
30 fluxed pellets, in particular fired iron ore fluxed pellets contain less than 10

%, in particular less than 5% weight of  $\text{SiO}_2$  with respect to the total weight of the pellets.

46. Fired metallic ore fluxed pellets, in particular crude iron ore fluxed pellets according to any one of claim 44 or claim 45, wherein the fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets comprise fine iron ore concentrate selected from the group consisting of magnetite, hematite and mixture thereof.

47. Fired metallic ore fluxed pellets, in particular fired iron ore fluxed pellets according to any one of claims 44 to 46, further comprising a flux selected from the group consisting of calcium carbonate, dolomite, olivine, pyroxenite, other magnesium silicates, like dunite, and mixture thereof.



**INTERNATIONAL SEARCH REPORT**

International application No  
PCT/EP2017/080986

A. CLASSIFICATION OF SUBJECT MATTER  
INV. C22B1/24 C22B1/243  
ADD.  
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED  
Minimum documentation searched (classification system followed by classification symbols)  
C22B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 3 008 405 A1 (LHOIST RECH & DEV SA [BE]) 16 January 2015 (2015-01-16) abstract page 1, line 22 - page 2, line 2 page 2, lines 20-30 page 3, lines 22-29 page 4, lines 17-24 page 16, line 19 - page 17, line 2 examples 2,8 claims 1,3,5,7,8,10,12,13-15,20,24,34	1-47
A	GB 990 672 A (KENNEDY VAN SAUN MFG & ENG) 28 April 1965 (1965-04-28) claims 1-9	1-47
A	EP 1 659 190 A2 (ISM INC [US]) 24 May 2006 (2006-05-24) the whole document	1-47

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search <b>27 February 2018</b>	Date of mailing of the international search report <b>12/03/2018</b>
--	---

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer <b>Riederer, Florian</b>
--	--

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/EP2017/080986
---

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
FR 3008405	A1	16-01-2015	AU 2014292228 A1	03-12-2015
			CA 2912499 A1	22-01-2015
			CN 105392738 A	09-03-2016
			DE 212014000154 U1	02-05-2016
			EA 201592180 A1	30-06-2016
			EP 3022154 A1	25-05-2016
			FR 3008405 A1	16-01-2015
			JP 2016531065 A	06-10-2016
			PH 12015502594 A1	29-02-2016
			SG 11201509435U A	30-03-2016
			TW 201522225 A	16-06-2015
			US 2016115076 A1	28-04-2016
			WO 2015007661 A1	22-01-2015
			ZA 201508558 B	29-11-2017
GB 990672	A	28-04-1965	DE 1227430 B	27-10-1966
			GB 990672 A	28-04-1965
EP 1659190	A2	24-05-2006	AR 051216 A1	27-12-2006
			AU 2005220202 A1	01-06-2006
			BR PI0504254 A	27-06-2006
			CA 2497614 A1	17-05-2006
			CN 1796577 A	05-07-2006
			CN 102061359 A	18-05-2011
			EP 1659190 A2	24-05-2006
			ES 2526696 T3	14-01-2015
			KR 20060055294 A	23-05-2006
			MX PA05008410 A	19-05-2006
			TW I280283 B	01-05-2007
			UA 84871 C2	10-12-2008
US 2006105901 A1	18-05-2006			